

NORYL™ RESIN WM230A

REGION ASIA

DESCRIPTION

NORYL WM230A resin is a 30% glass fiber reinforced blend of polyphenylene ether (PPE) + Polystyrene (PS). This injection moldable grade exhibits excellent long term hydrolytic stability, very low water absorption, heat / hot water resistance and is an excellent candidate for various water management applications such as pump housings, impellers and valves. See NORYL FE1630PW and WM330G resins for NSF /ANSI 61 and global potable water compliant versions.

GENERAL INFORMATION	
Features	Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Building and Construction	Water Management

TYPICAL PROPERTY VALUES

Revision 20241015

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	117	MPa	SABIC - Japan Method
Tensile Strain, break	8 – 10	%	SABIC - Japan Method
Flexural Stress	175.8	MPa	ASTM D790
Flexural Modulus	7780	MPa	ASTM D790
Hardness, Rockwell R	121	-	ASTM D785
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	146	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 6.4 mm, unannealed	141	°C	ASTM D648
CTE, -30°C to 30°C	0.00002 – 0.000043	1/°C	TMA
PHYSICAL ⁽¹⁾			
Specific Gravity	1.31	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.2 – 0.3	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	8.9	g/10 min	ASTM D1238
ELECTRICAL ⁽¹⁾			
Surface Resistivity	1.E+16	Ω	ASTM D257
Relative Permittivity, 50/60 Hz	2.93	-	ASTM D150

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.