LNP™ STAT-KON™ Compound REF42XXP

RCF-1006S

DESCRIPTION

LNP STAT-KON REF42XXP compound is based on Nylon 6/6 resin containing 20% glass fiber and 10% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber, Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break, 5 mm/min	189	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.1	%	ISO 527
Flexural Stress, break, 2 mm/min	250	MPa	ISO 178
Flexural Modulus, 2 mm/min	8700	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched 80*10*4 +23°C	60	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m²	ISO 180/1A
PHYSICAL [1]			
Mold Shrinkage on Tensile Bar, flow [2]	0.1 – 0.3	%	SABIC method
Density	1.32	g/cm³	ISO 1183
ELECTRICAL [1]			
Surface Resistivity [3]	1.E+03 – 1.E+05	Ω	ASTM D257
INJECTION MOLDING [4]			
Screw Speed	30 – 60	rpm	
Back Pressure	0.2 – 0.3	MPa	
Mold Temperature	95 – 110	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Melt Temperature	280 – 305	°C	
Maximum Moisture Content	0.15 – 0.25	%	
Drying Time	4	Hrs	

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	80	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved