

# ULTEM™ RESIN SF2250EPR

## DESCRIPTION

20% Glass fiber filled, super high flow polyetherimide(PEI) (TG 217degC) with internal mold release and balance properties with flow and ductility, ECO conforming, UL94 V0 listing.

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Flexural Stress, yld, 1.3 mm/min, 50 mm span	202	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	197	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7796	MPa	ASTM D790
Tensile Stress, brk, Type I, 5 mm/min	145	MPa	ASTM D638
Tensile Modulus, 5 mm/min	9057	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D638
Flexural Stress, yield, 2 mm/min	201	MPa	ISO 178
Flexural Stress, break, 2 mm/min	199	MPa	ISO 178
Flexural Modulus, 2 mm/min	7619	MPa	ISO 178
Tensile Stress, break, 5 mm/min	136	MPa	ISO 527
Tensile Modulus, 1 mm/min	8747	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.3	%	ISO 527
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	79.7	J/m	ASTM D256
Izod Impact, unnotched, 23°C	368	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	8.8	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8.5	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	35	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 3.2mm, unannealed	201	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	198	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	207	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	205	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	203	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	209	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	212	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	213	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	210	°C	ISO 306
Vicat Softening Temp, Rate B/120	211	°C	ISO 306
CTE, -40°C to 150°C, flow	2.3E-05	1/°C	ASTM E831
CTE, -40°C to 150°C, xflow	5.4E-05	1/°C	ASTM E831
CTE, 23°C to 150°C, flow	2.0E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	7.0E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec <sup>(2)</sup>	105	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Mech w/impact <sup>(2)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	105	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.4314	g/cm <sup>3</sup>	ISO 1183
Mold Shrinkage, flow <sup>(3)</sup>	0.3833	%	SABIC method
Mold Shrinkage, xflow <sup>(3)</sup>	0.4466	%	SABIC method
Moisture Absorption, (23°C/50% RH/24hrs)	0.05	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.136	%	ASTM D570
Specific Gravity	1.4314	-	ASTM D792
Melt Volume Rate, MVR at 360°C/2.16 kg	12	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 337°C/6.7 kg	21	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 345°C/10.0 kg	57	cm <sup>3</sup> /10 min	ISO 1133
Melt Flow Rate, 360°C/2.16 kgf	12.9	g/10 min	ASTM D1238
Melt Flow Rate, 337°C/6.7 kgf	21.9	g/10 min	ASTM D1238
Melt Flow Rate, 345°C/10 kgf	56	g/10 min	ASTM D1238
<b>ELECTRICAL <sup>(1)</sup></b>			
<b>Dielectric Constant</b>			
1.1 GHz	3.382	-	SABIC method
5 GHz	3.353	-	SABIC method
10 GHz	3.344	-	SABIC method
15 GHz	3.397	-	SABIC method
<b>Dissipation Factor</b>			
1.1 GHz	0.0020	-	SABIC method
5 GHz	0.0024	-	SABIC method
10 GHz	0.0031	-	SABIC method
15 GHz	0.0035	-	SABIC method
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-104394172</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5 – 1.6	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	345 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.