

LNPT[™] THERMOCOMP[™] COMPOUND WF0069

WF-1006 FR-S

DESCRIPTION

LNP THERMOCOMP WF0069 compound is based on Polybutylene Terephthalate (PBT) resin containing 30% glass fiber. Added features of this grade include: Flame Retardant.

GENERAL INFORMATION	
Features	Flame Retardant, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Flexural Strength, 1.3 mm/min, 50 mm span	165	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	9650	MPa	ASTM D790
Tensile Stress, brk, Type I, 5 mm/min	121	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D638
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	370	J/m	ASTM D4812
Izod Impact, notched, 23°C	64	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	204	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.68	g/cm ³	ASTM D792
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.4 – 0.5	%	ASTM D955
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-101358191	-	-
UL Recognized, 94V-0 Flame Class Rating	0.73	mm	UL 94
INJECTION MOLDING ⁽³⁾			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	230 – 255	°C	
Front - Zone 3 Temperature	240 – 260	°C	
Middle - Zone 2 Temperature	235 – 250	°C	
Rear - Zone 1 Temperature	230 – 240	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.