

# LNPT<sup>TM</sup> THERMOCOMP<sup>TM</sup> COMPOUND DC0041PE

## DESCRIPTION

LNP THERMOCOMP COMPOUND DC0041PE is a compound based on Polycarbonate resin containing Carbon Fiber. Added feature of this grade is: Flame Retardant, PCR content up to 30%

GENERAL INFORMATION	
Features	Flame Retardant, Sustainable (Mechanical Recycling), Non Cl/Br flame retardant, Carbon fiber filled, Dimensional stability, High stiffness/Strength
Fillers	Carbon Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Mobile Phone - Computer - Tablets

## TYPICAL PROPERTY VALUES

Revision 20240313

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, brk, Type I, 5 mm/min	165	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.4	%	ASTM D638
Tensile Modulus, 5 mm/min	18100	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	223	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	16600	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	167	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	18500	MPa	ISO 527
Flexural Strength, 2 mm/min	214	MPa	ISO 178
Flexural Modulus, 2 mm/min	16800	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	57	J/m	ASTM D256
Izod Impact, notched, -30°C	50	J/m	ASTM D256
Izod Impact, unnotched, 23°C	380	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	383	J/m	ASTM D4812
Izod Impact, notched 80*10*3 +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*3 +23°C	31	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	35	kJ/m <sup>2</sup>	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	8	kJ/m <sup>2</sup>	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	7	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	31	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	36	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	33	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	39	kJ/m <sup>2</sup>	ISO 179/1eU
Instrumented Dart Impact Total Energy, 23°C	11	J	ASTM D3763
Instrumented Dart Impact Energy @ peak, 23°C	10	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	106	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	100	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	108	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	101	°C	ISO 75/Af
CTE, -40°C to 40°C, flow	6.8E-6	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.8E-5	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	6.9E-6	1/°C	ASTM E831
CTE, 23°C to 80°C, xflow	6.8E-5	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	5.3E-6	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.2E-5	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	6.3E-6	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	6.8E-5	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	108	°C	ISO 306
Vicat Softening Temp, Rate B/120	110	°C	ISO 306
Relative Temp Index, Elec <sup>(2)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	80	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Melt Volume Rate, MVR at 300°C/2.16 kg	27	cm <sup>3</sup> /10 min	ASTM D1238
Specific Gravity	1.29	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.03	%	ISO 62-1
Mold Shrinkage, flow <sup>(3)</sup>	0.06	%	SABIC method
Mold Shrinkage, xflow <sup>(3)</sup>	0.1	%	SABIC method
<b>ELECTRICAL <sup>(1)</sup></b>			
Surface Resistivity	1.0E+6	Ω	ASTM D257
Volume Resistivity	1.0E+6	Ω.cm	ASTM D257
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-104237180</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.80	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	70	°C	
Drying Time	4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 330	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	280 – 320	°C	
Middle - Zone 2 Temperature	270 – 310	°C	
Rear - Zone 1 Temperature	260 – 300	°C	
Mold Temperature	60 – 85	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 63	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.