

LNPTM STAT-KONTM COMPOUND DX09303C

DESCRIPTION

LNP STAT-KON DX09303C compound is based on Polycarbonate (PC) resin containing 35% carbon fiber. Added features of this grade include: LNP Clean Compounding Technology, Low LPC, Low Ionics, Low Outgassing, Low C18-C40 Hydrocarbons, Electrically Conductive, High Modulus, Good Flow.

GENERAL INFORMATION	
Features	Electrically Conductive, Good Processability, Low ionics/Outgassing/Liquid particle count, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	161	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Tensile Modulus, 5 mm/min	20130	MPa	ASTM D638
Flexural Stress	246	MPa	ASTM D790
Flexural Modulus	18000	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	601	J/m	ASTM D4812
Izod Impact, notched, 23°C	82	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	125	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.4E-06	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.98E-05	1/°C	ASTM E831
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.35	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.05 – 0.15	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽³⁾	0.1 – 0.25	%	SABIC method
Melt Volume Rate, MVR at 300°C/5.0 kg	47	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽⁴⁾	5.E+03 – 5.E+05	Ω	ASTM D257

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-101095846	-	-
UL Recognized, 94HB Flame Class Rating	≥1	mm	UL 94
INJECTION MOLDING ⁽⁵⁾			
Drying Temperature	90 – 110	°C	
Drying Time	3 – 5	Hrs	
Melt Temperature	280 – 320	°C	
Nozzle Temperature	280 – 320	°C	
Front - Zone 3 Temperature	280 – 320	°C	
Middle - Zone 2 Temperature	280 – 320	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Mold Temperature	90 – 120	°C	
Back Pressure	1 – 5	MPa	
Screw Speed	30 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Measurement meets requirements as specified in ASTM D4496.

(5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.