

# LNPTM ELCRINTM WF006NAiQ2

ER015842

## DESCRIPTION

LNP ELCRIN WF006NAiQ2 is an iQ PBT Generation 2 based compound containing 30% glass for NMT applications. Added features of this material include : >25% PCR, high flow, low warpage, high metal bonding strength and good chemical resistance.

| GENERAL INFORMATION   |                                                                                                                                                                                                                                                                                  |
|-----------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Features              | Chemical Resistance, Good Processability, Heat Stabilized, High Flow, Low Warpage, UV-C resistant, Advanced Recycling, Enhanced mold release, Nano molding technology, High stiffness/Strength, No PFAS intentionally added (PCR contains <50ppm total organic fluorine content) |
| Fillers               | Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)                                                                                                                                                                                                                 |
| Polymer Types         | Polybutylene Terephthalate (PBT)                                                                                                                                                                                                                                                 |
| Processing Techniques | Injection Molding                                                                                                                                                                                                                                                                |

  

| INDUSTRY                   | SUB INDUSTRY                      |
|----------------------------|-----------------------------------|
| Consumer                   | Commercial Appliance              |
| Electrical and Electronics | Mobile Phone - Computer - Tablets |
| Industrial                 | Electrical                        |

## TYPICAL PROPERTY VALUES

Revision 20260908

| PROPERTIES                                   | TYPICAL VALUES | UNITS             | TEST METHODS |
|----------------------------------------------|----------------|-------------------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>             |                |                   |              |
| Tensile Stress, brk, Type I, 5 mm/min        | 106            | MPa               | ASTM D638    |
| Tensile Strain, brk, Type I, 5 mm/min        | 2.6            | %                 | ASTM D638    |
| Tensile Modulus, 5 mm/min                    | 8240           | MPa               | ASTM D638    |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 163            | MPa               | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 7320           | MPa               | ASTM D790    |
| Tensile Stress, break, 5 mm/min              | 110            | MPa               | ISO 527      |
| Tensile Strain, break, 5 mm/min              | 2.6            | %                 | ISO 527      |
| Tensile Stress, yield, 5 mm/min              | 111            | MPa               | ISO 527      |
| Tensile Modulus, 1 mm/min                    | 8290           | MPa               | ISO 527      |
| Flexural Modulus, 2 mm/min                   | 7820           | MPa               | ISO 178      |
| Flexural Stress, break, 2 mm/min             | 170            | MPa               | ISO 178      |
| <b>IMPACT <sup>(1)</sup></b>                 |                |                   |              |
| Instrumented Dart Impact Total Energy, 23°C  | 23             | J                 | ASTM D3763   |
| Instrumented Dart Impact Energy @ peak, 23°C | 12             | J                 | ASTM D3763   |
| Instrumented Dart Impact Peak Force, 23°C    | 1600           | N                 | ASTM D3763   |
| Izod Impact, unnotched, 23°C                 | 831            | J/m               | ASTM D4812   |
| Izod Impact, notched, 23°C                   | 138            | J/m               | ASTM D256    |
| Izod Impact, notched, -30°C                  | 95             | J/m               | ASTM D256    |
| Izod Impact, unnotched 80*10*4 +23°C         | 70             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C           | 15             | kJ/m <sup>2</sup> | ISO 180/1A   |

| PROPERTIES                                              | TYPICAL VALUES                    | UNITS      | TEST METHODS |
|---------------------------------------------------------|-----------------------------------|------------|--------------|
| Izod Impact, notched 80*10*4 -30°C                      | 11                                | kJ/m²      | ISO 180/1A   |
| <b>THERMAL <sup>(1)</sup></b>                           |                                   |            |              |
| Vicat Softening Temp, Rate B/120                        | 162                               | °C         | ASTM D1525   |
| Vicat Softening Temp, Rate B/50                         | 158                               | °C         | ASTM D1525   |
| HDT, 1.82 MPa, 3.2mm, unannealed                        | 161                               | °C         | ASTM D648    |
| HDT, 0.45 MPa, 3.2 mm, unannealed                       | 214                               | °C         | ASTM D648    |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm                   | 174                               | °C         | ISO 75/Af    |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm                  | 216                               | °C         | ISO 75/Bf    |
| CTE, -40°C to 40°C, flow                                | 2.3E-05                           | 1/°C       | ASTM E831    |
| CTE, -40°C to 40°C, xflow                               | 1.4E-04                           | 1/°C       | ASTM E831    |
| <b>PHYSICAL <sup>(1)</sup></b>                          |                                   |            |              |
| Moisture Absorption, (23°C/50% RH/24hrs) <sup>(2)</sup> | 0.02                              | %          | ISO 62-4     |
| Water Absorption, (23°C/24hrs) <sup>(2)</sup>           | 0.06                              | %          | ISO 62-1     |
| Specific Gravity                                        | 1.53                              | -          | ASTM D792    |
| Density                                                 | 1.53                              | g/cm³      | ISO 1183     |
| <b>Melt Flow Rate</b>                                   |                                   |            |              |
| 250°C/5.0 kgf                                           | 10                                | g/10 min   | ASTM D1238   |
| 275°C/5 kgf                                             | 19                                | g/10 min   | ASTM D1238   |
| <b>Melt Volume Rate</b>                                 |                                   |            |              |
| 250°C/5.0 kg                                            | 8                                 | cm³/10 min | ISO 1133     |
| 275°C/5 kg                                              | 14                                | cm³/10 min | ISO 1133     |
| Mold Shrinkage, flow <sup>(3)</sup>                     | 0.1 – 0.2                         | %          | SABIC method |
| Mold Shrinkage, xflow <sup>(3)</sup>                    | 0.2 – 0.3                         | %          | SABIC method |
| <b>ELECTRICAL <sup>(1)</sup></b>                        |                                   |            |              |
| <b>Dielectric Constant</b>                              |                                   |            |              |
| 1.1 GHz                                                 | 3.60                              | -          | SABIC method |
| 2.45 GHz                                                | 3.60                              | -          | SABIC method |
| 5 GHz                                                   | 3.58                              | -          | SABIC method |
| 10 GHz                                                  | 3.58                              | -          | SABIC method |
| <b>Dissipation Factor</b>                               |                                   |            |              |
| 1.1 GHz                                                 | 0.013                             | -          | SABIC method |
| 2.45 GHz                                                | 0.012                             | -          | SABIC method |
| 5 GHz                                                   | 0.011                             | -          | SABIC method |
| 10 GHz                                                  | 0.009                             | -          | SABIC method |
| <b>FLAME CHARACTERISTICS <sup>(4)</sup></b>             |                                   |            |              |
| UL Yellow Card Link                                     | <a href="#">E207780-104552483</a> | -          | -            |
| UL Recognized, 94HB Flame Class Rating                  | ≥0.7                              | mm         | UL 94        |
| <b>INJECTION MOLDING <sup>(5)</sup></b>                 |                                   |            |              |
| Drying Temperature                                      | 110 – 120                         | °C         |              |
| Drying Time                                             | 2 – 4                             | Hrs        |              |
| Drying Time (Cumulative)                                | 8                                 | Hrs        |              |
| Maximum Moisture Content                                | 0.02                              | %          |              |
| Melt Temperature                                        | 250 – 270                         | °C         |              |
| Nozzle Temperature                                      | 245 – 275                         | °C         |              |
| Front - Zone 3 Temperature                              | 250 – 270                         | °C         |              |

| PROPERTIES                      | TYPICAL VALUES | UNITS | TEST METHODS |
|---------------------------------|----------------|-------|--------------|
| Middle - Zone 2 Temperature     | 250 – 270      | °C    |              |
| Rear - Zone 1 Temperature       | 240 – 260      | °C    |              |
| Hopper Temperature              | 40 – 60        | °C    |              |
| Mold Temperature <sup>(6)</sup> | 100 – 160      | °C    |              |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Based on internal method similar to ISO 62
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.
- (6) Suggest to use narrow mold temperature 140C~160C for NMT application.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.