

# NORYL™ RESIN PX2938

REGION ASIA

## DESCRIPTION

NORYL PX2938 resin is a 20% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection molding and extrusion grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of VO at 0.75mm. NORYL PX2938 resin exhibits high heat resistance, high impact strength, dimensional stability, hydrolytic stability, and very low moisture absorption. This material is an excellent candidate for industrial applications such as cooling fans.

### GENERAL INFORMATION

<b>Features</b>	Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
<b>Fillers</b>	Glass Fiber
<b>Polymer Types</b>	Polyphenylene Ether + PS (PPE+PS)
<b>Processing Techniques</b>	Injection Molding

### INDUSTRY

Building and Construction  
Electrical and Electronics  
Hygiene and Healthcare  
Industrial

### SUB INDUSTRY

Building Component, Water Management  
Mobile Phone - Computer - Tablets  
Patient Testing  
Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	107	MPa	SABIC - Japan Method
Tensile Strain, break	8 – 8	%	SABIC - Japan Method
Flexural Stress	143	MPa	ASTM D790
Flexural Modulus	5640	MPa	ASTM D790
Hardness, Rockwell R	127	-	ASTM D785
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	87	J/m	ASTM D256
Izod Impact, notched, -30°C	85	J/m	ASTM D256
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	143	°C	ASTM D648
CTE, -30°C to 30°C	0.000027 – 0.000044	1/°C	TMA
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.26	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.2 – 0.4	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	19.8	g/10 min	ASTM D1238
<b>INJECTION MOLDING <sup>(3)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 325	°C	
Nozzle Temperature	300 – 325	°C	
Front - Zone 3 Temperature	290 – 325	°C	
Middle - Zone 2 Temperature	275 – 320	°C	
Rear - Zone 1 Temperature	265 – 315	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.