

# LEXAN™ COPOLYMER FST3403T

REGION AMERICAS

## DESCRIPTION

LEXAN FST3403T is based on Polycarbonate (PC) copolymer high flow resin suitable for injection molding. This halogen-free flame retardant resin is EN45545 compliant and is an ideal candidate for train interior applications such as cladding with an R1 / HL3 rating (e.g. side panels & partition walls) and seating with an R6 / HL3 rating (e.g. back & base shells). It also meets requirements of NFPA-130 standards. Available in transparent and opaque colors.

## TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 50 mm/min	77	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	70	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	75	%	ASTM D638
Tensile Modulus, 5 mm/min	2600	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	115	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2700	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	77	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	95	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	105	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	120	J/m	ASTM D256
Izod Impact, notched, -30°C	85	J/m	ASTM D256
Multiaxial Impact	130	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	60	J	ASTM D3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL <sup>(1)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	104	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	94	°C	ISO 75/Af
Vicat Softening Temp, Rate B/50	111	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	104	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	94	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/120	113	°C	ISO 306
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.33	-	ASTM D792
Mold Shrinkage, flow <sup>(2)</sup>	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow <sup>(2)</sup>	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	12	g/10 min	ASTM D1238
Density	1.33	g/cm <sup>3</sup>	ISO 1183
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm <sup>3</sup> /10 min	ISO 1133
<b>FLAME CHARACTERISTICS</b>			
Flame Spread Index (1.52mm)	<35	-	ASTM E162
NBS Smoke Density, Flaming, Ds 1.5 min	<100	-	ASTM E662
NBS Smoke Density, Flaming, Ds 4 min	<200	-	ASTM E662
Heat release, MAHRE, 50 kW/m <sup>2</sup> <sup>(3)</sup>	<60	kW/m <sup>2</sup>	ISO 5660-1
Smoke Toxicity	PASSES	-	OEM BSS
Smoke density, DS-4, 50 kW/m <sup>2</sup> <sup>(3)</sup>	<150	-	ISO 5659-2
Smoke density, VOF4, 50 kW/m <sup>2</sup> <sup>(3)</sup>	<300	-	ISO 5659-2
Smoke toxicity, CITG (8 min), 50 kW/m <sup>2</sup> <sup>(3)</sup>	0.1	-	ISO 5659-2
Fire Safety Hazard Level - Requirement set R6 <sup>(4)</sup>	HL3	-	EN 45545-2
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Drying Temperature	95 – 100	°C	
Drying Time	6 – 8	Hrs	
Melt Temperature	250 – 280	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	250 – 280	°C	
Middle - Zone 2 Temperature	240 – 270	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	50 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (3) 3 mm
- (4) based on EN 45545-2: 2013 revision
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.