

# LNPT<sup>™</sup> THERMOCOMP<sup>™</sup> COMPOUND EC006APQ

EC006APQ

## DESCRIPTION

LNP THERMOCOMP EC006APQ compound is based on Polyetherimide (PEI) resin containing 30% carbon fiber. Added features of this grade include: Electrically Conductive, High Flow, FAR25.853 Compliant.

| GENERAL INFORMATION   |                                                                                                                                                             |
|-----------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Features              | Flame Retardant, Electrically Conductive, High Flow, Carbon fiber filled, High stiffness/Strength, High temperature resistance, No PFAS intentionally added |
| Fillers               | Carbon Fiber                                                                                                                                                |
| Polymer Types         | Polyetherimide (PEI)                                                                                                                                        |
| Processing Techniques | Injection Molding                                                                                                                                           |

  

| INDUSTRY                  | SUB INDUSTRY                         |
|---------------------------|--------------------------------------|
| Automotive                | Automotive Under the Hood, Aerospace |
| Building and Construction | Building Component                   |
| Consumer                  | Sport/Leisure                        |
| Industrial                | Electrical                           |

## TYPICAL PROPERTY VALUES

Revision 20260731

| PROPERTIES                                   | TYPICAL VALUES | UNITS | TEST METHODS |
|----------------------------------------------|----------------|-------|--------------|
| MECHANICAL <sup>(1)</sup>                    |                |       |              |
| Tensile Stress, break, 5 mm/min              | 252            | MPa   | ISO 527      |
| Tensile Strain, break, 5 mm/min              | 1.1            | %     | ISO 527      |
| Tensile Modulus, 1 mm/min                    | 29250          | MPa   | ISO 527      |
| Flexural Stress                              | 332            | MPa   | ISO 178      |
| Flexural Modulus, 2 mm/min                   | 23930          | MPa   | ISO 178      |
| Tensile Stress, brk, Type I, 5 mm/min        | 281            | MPa   | ASTM D638    |
| Tensile Strain, brk, Type I, 5 mm/min        | 1.1 – 1.3      | %     | ASTM D638    |
| Tensile Modulus, 5 mm/min                    | 30520          | MPa   | ASTM D638    |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 350            | MPa   | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 26300          | MPa   | ASTM D790    |
| Shear Modulus                                | 4726           | MPa   | ASTM D732    |
| Shear Strength                               | 128            | MPa   | ASTM D732    |
| Compressive Strength                         | 231            | MPa   | SABIC method |
| IMPACT <sup>(1)</sup>                        |                |       |              |
| Izod Impact, unnotched, 23°C                 | 713            | J/m   | ASTM D4812   |
| Izod Impact, notched, 23°C                   | 82             | J/m   | ASTM D256    |
| THERMAL <sup>(1)</sup>                       |                |       |              |
| HDT, 1.82 MPa, 3.2mm, unannealed             | 195            | °C    | ASTM D648    |
| CTE, -40°C to 150°C, flow                    | 5.0E-06        | 1/°C  | ASTM E831    |

| PROPERTIES                                | TYPICAL VALUES | UNITS    | TEST METHODS |
|-------------------------------------------|----------------|----------|--------------|
| CTE, -40°C to 150°C, xflow                | 7.0E-06        | 1/°C     | ASTM E83 1   |
| <b>PHYSICAL <sup>(1)</sup></b>            |                |          |              |
| Specific Gravity                          | 1.39           | -        | ASTM D792    |
| Moisture Absorption, (23°C/50% RH/24 hrs) | 0.11           | %        | ASTM D570    |
| Mold Shrinkage, flow                      | 0.03           | %        | SABIC method |
| Mold Shrinkage, xflow                     | 0.1            | %        | SABIC method |
| <b>Melt Flow Rate</b>                     |                |          |              |
| 380°C/6.7 kgf                             | 69             | g/10 min | ASTM D1238   |
| Poisson's Ratio                           | 0.44           | -        | ASTM E132    |
| <b>ELECTRICAL <sup>(1)</sup></b>          |                |          |              |
| Surface Resistivity                       | 1.E+03         | Ω        | ASTM D257    |
| <b>INJECTION MOLDING <sup>(2)</sup></b>   |                |          |              |
| Drying Temperature                        | 150            | °C       |              |
| Drying Time                               | 4 – 6          | Hrs      |              |
| Maximum Moisture Content                  | 0.02           | %        |              |
| Melt Temperature                          | 360 – 400      | °C       |              |
| Rear - Zone 1 Temperature                 | 360 – 380      | °C       |              |
| Middle - Zone 2 Temperature               | 370 – 390      | °C       |              |
| Front - Zone 3 Temperature                | 380 – 400      | °C       |              |
| Nozzle Temperature                        | 390 – 400      | °C       |              |
| Mold Temperature                          | 140 – 180      | °C       |              |
| Back Pressure                             | 0.3 – 0.7      | MPa      |              |
| Screw speed (Circumferential speed)       | 0.2 – 0.3      | m/s      |              |
| Vent Depth                                | 0.025 – 0.076  | mm       |              |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.