

NORYL™ RESIN GFN3

REGION EUROPE

DESCRIPTION

NORYL GFN3 resin is a 30% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This general-purpose injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN3 carries a UL746C outdoor suitability rating of F2 and is an excellent candidate for a variety of indoor and outdoor applications including construction, electrical components + displays, lawn and garden equipment. *See NORYL GFN3F resin for FDA food compliant / NSF version.

| GENERAL INFORMATION | |
|-----------------------|--|
| Features | Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added |
| Fillers | Glass Fiber |
| Polymer Types | Polyphenylene Ether + PS (PPE+PS) |
| Processing Techniques | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|----------------------------|--|
| Building and Construction | Building Component |
| Consumer | Commercial Appliance |
| Electrical and Electronics | Electronic Components, Mobile Phone - Computer - Tablets |

TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-------------------|----------------|
| MECHANICAL ⁽¹⁾ | | | |
| Taber Abrasion, CS-17, 1 kg | 70 | mg/1000cy | SABIC method |
| Tensile Stress, break, 5 mm/min | 100 | MPa | ISO 527 |
| Tensile Strain, break, 5 mm/min | 1.5 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 8000 | MPa | ISO 527 |
| Flexural Stress, break, 2 mm/min | 125 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 6000 | MPa | ISO 178 |
| Ball Indentation Hardness, H358/30 | 130 | MPa | ISO 2039-1 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, unnotched 80*10*4 +23°C | 25 | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*4 -30°C | 25 | kJ/m ² | ISO 180/1U |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | 25 | kJ/m ² | ISO 179/1eU |
| Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm | 25 | kJ/m ² | ISO 179/1eU |
| THERMAL ⁽¹⁾ | | | |
| Thermal Conductivity | 0.28 | W/m.°C | ISO 8302 |
| CTE, 23°C to 80°C, flow | 3.E-05 | 1/°C | ISO 11359-2 |
| CTE, 23°C to 80°C, xflow | 7.E-05 | 1/°C | ISO 11359-2 |
| Ball Pressure Test, 125°C +/- 2°C | PASSES | - | IEC 60695-10-2 |
| Ball Pressure Test, approximate maximum | 125 | °C | IEC 60695-10-2 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|-------------------------------|-------------------------|----------------|
| Vicat Softening Temp, Rate A/50 | 155 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/50 | 145 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 155 | °C | ISO 306 |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm | 145 | °C | ISO 75/Be |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm | 140 | °C | ISO 75/Ae |
| Relative Temp Index, Elec ⁽²⁾ | 65 | °C | UL 746B |
| Relative Temp Index, Mech w/impact ⁽²⁾ | 65 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact ⁽²⁾ | 65 | °C | UL 746B |
| PHYSICAL ⁽¹⁾ | | | |
| Mold Shrinkage on Tensile Bar, flow ⁽³⁾ | 0.1 – 0.3 | % | SABIC method |
| Density | 1.3 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/saturated) | 0.2 | % | ISO 62-1 |
| Moisture Absorption (23°C / 50% RH) | 0.06 | % | ISO 62 |
| Melt Volume Rate, MVR at 280°C/ 10.0 kg | 7 | cm ³ /10 min | ISO 1133 |
| ELECTRICAL ⁽¹⁾ | | | |
| Volume Resistivity | 1.E+15 | Ω.cm | IEC 60093 |
| Surface Resistivity, ROA | >1.E+15 | Ω | IEC 60093 |
| Dielectric Strength, in oil, 3.2 mm | 18 | kV/mm | IEC 60243-1 |
| Relative Permittivity, 1 MHz | 2.9 | - | IEC 60250 |
| Dissipation Factor, 50/60 Hz | 0.0006 | - | IEC 60250 |
| Dissipation Factor, 1 MHz | 0.001 | - | IEC 60250 |
| Comparative Tracking Index ⁽⁴⁾ | 250 | V | IEC 60112 |
| Relative Permittivity, 50/60 Hz | 2.9 | - | IEC 60250 |
| FLAME CHARACTERISTICS ⁽²⁾ | | | |
| UL Yellow Card Link | E45329-236756 | - | - |
| UL Recognized, 94HB Flame Class Rating | 1.5 | mm | UL 94 |
| Glow Wire Flammability Index 850°C, passes at ⁽⁴⁾ | 3.2 | mm | IEC 60695-2-12 |
| Oxygen Index (LOI) | 26 | % | ISO 4589 |
| INJECTION MOLDING ⁽⁵⁾ | | | |
| Drying Temperature | 100 – 120 | °C | |
| Drying Time | 2 – 4 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 280 – 300 | °C | |
| Nozzle Temperature | 280 – 300 | °C | |
| Front - Zone 3 Temperature | 290 – 310 | °C | |
| Middle - Zone 2 Temperature | 270 – 290 | °C | |
| Rear - Zone 1 Temperature | 250 – 270 | °C | |
| Hopper Temperature | 60 – 80 | °C | |
| Mold Temperature | 80 – 120 | °C | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Value shown here is based on internal measurement.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.