

# LNPT<sup>TM</sup> THERMOCOMP<sup>TM</sup> COMPOUND 9X10312

## DESCRIPTION

LNP THERMOCOMP 9X10312 compound is based on Nylon blend containing 50% glass fiber. Added features of this grade include: Impact Modified, High Flow, Good Ductility, Low Moisture Absorption.

GENERAL INFORMATION	
Features	High Flow, Low Moisture Absorption, High stiffness/Strength, Impact resistant
Fillers	Glass Fiber
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, brk, Type I, 5 mm/min	212	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.8	%	ASTM D638
Tensile Modulus, 5 mm/min	15000	MPa	ASTM D638
Flexural Stress	310	MPa	ASTM D790
Flexural Modulus	13000	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	150	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	12	J	ASTM D3763
Charpy 23°C, V-notch Edgew 80°10*3 sp=62mm	16	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 3.2mm, unannealed	250	°C	ASTM D648
Relative Temp Index, Elec	65	°C	UL 746B
Relative Temp Index, Mech w/impact	65	°C	UL 746B
Relative Temp Index, Mech w/o impact	65	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.55	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.12	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm <sup>(2)</sup>	0.44	%	SABIC method
Water Absorption, (23°C/saturated)	0.8	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/2.16 kg	15	cm <sup>3</sup> /10 min	ISO 1133

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>ELECTRICAL <sup>(1)</sup></b>			
Dielectric Constant (Dk), 1.1 GHz	4	-	ASTM ES 7-83
Dissipation Factor (Df), 1.1 GHz	0.01	-	ASTM ES 7-83
<b>FLAME CHARACTERISTICS <sup>(3)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-101337256</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥0.8	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.