# LNP™ ELCRIN™ DF0041RC1

(ER015716)

## DESCRIPTION

LNP ELCRIN DF0041RC1 compound is based on recycled polycarbonate (PC) resin containing 20% pre-consumer recycled glass fiber. Added features of this grade include: high modulus, non-brominated and non-chlorinated flame retardant. Post-consumer recycled (PCR) polycarbonate content up to 40%. Total recycle content up to 60%. Available in black colors.

| GENERAL INFORMATION | |
|---|---|
| **Features** | Structural, Flame Retardant, Non-Brominated, Non-Chlorinated, Mechanical Recycling |
| **Fillers** | Glass Fiber |
| **Brands** | LNP™ ELCRIN™ |
| **Polymer Types** | Polycarbonate (PC) |
| **Processing Techniques** | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|---|---|
| Building and Construction | Outdoor, Lawn and Landscape |
| Consumer | Personal Accessory |
| Electrical and Electronics | Electrical Devices and Displays, Electrical Components and Infrastructure |

## TYPICAL PROPERTY VALUES

Revision 20260907

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| MECHANICAL [1] | | | |
| **Tensile Stress, yield, 5 mm/min** | 108 | MPa | ISO 527 |
| **Tensile Stress, break, 5 mm/min** | 106 | MPa | ISO 527 |
| **Tensile Strain, yield, 5 mm/min** | 3.1 | % | ISO 527 |
| **Tensile Strain, break, 5 mm/min** | 3.4 | % | ISO 527 |
| **Tensile Modulus, 1 mm/min** | 6000 | MPa | ISO 527 |
| **Flexural Stress, break, 2 mm/min** | 173 | MPa | ISO 178 |
| **Flexural Modulus, 2 mm/min** | 6100 | MPa | ISO 178 |
| **Tensile Stress, yld, Type I, 5 mm/min** | 110 | MPa | ASTM D638 |
| **Tensile Stress, brk, Type I, 5 mm/min** | 104 | MPa | ASTM D638 |
| **Tensile Strain, yld, Type I, 5 mm/min** | 3.1 | % | ASTM D638 |
| **Tensile Strain, brk, Type I, 5 mm/min** | 3.5 | % | ASTM D638 |
| **Tensile Modulus, 5 mm/min** | 6100 | MPa | ASTM D638 |
| **Flexural Stress, yld, 1.3 mm/min, 50 mm span** | 177 | MPa | ASTM D790 |
| **Flexural Stress, brk, 1.3 mm/min, 50 mm span** | 177 | MPa | ASTM D790 |
| **Flexural Modulus, 1.3 mm/min, 50 mm span** | 5800 | MPa | ASTM D790 |
| IMPACT [1] | | | |
| **Izod Impact, notched 80*10*4 +23°C** | 16 | kJ/m² | ISO 180/1A |
| **Izod Impact, notched 80*10*4 -30°C** | 12 | kJ/m² | ISO 180/1A |
| **Izod Impact, unnotched 80*10*4 +23°C** | 54 | kJ/m² | ISO 180/1U |

© 2026 Copyright by SABIC. All rights reserved

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| Izod Impact, unnotched 80*10*4 -30°C | 59 | kJ/m² | ISO 180/1U |
| Izod Impact, unnotched, 23°C | 740 | J/m | ASTM D4812 |
| Izod Impact, unnotched, -30°C | 840 | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 105 | J/m | ASTM D256 |
| Izod Impact, notched, -30°C | 100 | J/m | ASTM D256 |
| Instrumented Impact Total Energy, 23°C | 26 | J | ASTM D3763 |
| Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm | 16 | kJ/m² | ISO 179/1eA |
| Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm | 10 | kJ/m² | ISO 179/1eA |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | 58 | kJ/m² | ISO 179/1eU |
| THERMAL [1] | | | |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 124 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 119 | °C | ISO 75/Af |
| Vicat Softening Temp, Rate B/50 | 125 | °C | ASTM D1525 |
| Vicat Softening Temp, Rate B/120 | 128 | °C | ASTM D1525 |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 123 | °C | ASTM D648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 119 | °C | ASTM D648 |
| CTE, -40°C to 40°C, flow | 2.8E-05 | 1/°C | ASTM E831 |
| CTE, -40°C to 40°C, xflow | 8.0E-05 | 1/°C | ASTM E831 |
| PHYSICAL [1] | | | |
| Density | 1.34 | g/cm³ | ISO 1183 |
| Melt Volume Rate, MVR at 300°C/1.2 kg | 8 | cm³/10 min | ISO 1133 |
| Melt Volume Rate, MVR at 300°C/2.16 kg | 16 | cm³/10 min | ISO 1133 |
| Specific Gravity | 1.35 | - | ASTM D792 |
| Mold Shrinkage, flow [2] | 0.3 – 0.5 | % | SABIC method |
| Mold Shrinkage, xflow [2] | 0.3 – 0.5 | % | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf | 9 | g/10 min | ASTM D1238 |
| Melt Flow Rate, 300°C/2.16 kgf | 20 | g/10 min | ASTM D1238 |
| FLAME CHARACTERISTICS [3] | | | |
| UL Yellow Card Link | E207780-104593870 | - | - |
| UL Recognized, 94V-0 Flame Class Rating | ≥0.6 | mm | UL 94 |
| ELECTRICAL PROPERTIES [1] | | | |
| Dielectric Constant [1] | | | |
| 1.1 GHz | 3.21 | - | SABIC method |
| 2.5 GHz | 3.22 | - | SABIC method |
| 5 GHz | 3.22 | - | SABIC method |
| 10 GHz | 3.22 | - | SABIC method |
| Dissipation Factor [1] | | | |
| 1.1 GHz | 0.006 | - | SABIC method |
| 2.5 GHz | 0.007 | - | SABIC method |
| 5 GHz | 0.007 | - | SABIC method |
| 10 GHz | 0.007 | - | SABIC method |
| INJECTION MOLDING [4] | | | |
| Drying Temperature | 110 | °C | |
| Drying Time | 3 – 6 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |

© 2026 Copyright by SABIC. All rights reserved

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| **Melt Temperature** | 285 – 310 | °C | |
| **Nozzle Temperature** | 285 – 305 | °C | |
| **Front - Zone 3 Temperature** | 280 – 300 | °C | |
| **Middle - Zone 2 Temperature** | 270 – 290 | °C | |
| **Rear - Zone 1 Temperature** | 260 – 280 | °C | |
| **Mold Temperature** | 80 – 110 | °C | |
| **Back pressure (Plastic Pressure)** | 0.1 – 0.3 | MPa | |
| **Screw Speed** | 50 – 90 | rpm | |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded articles.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved