

LNPT[™] ELCREST[™] DMX6034

DESCRIPTION

ELCREST DMX6034 is an impact modified, improved scratch resistant polycarbonate copolymer. This medium flow, UV stabilized, custom colorable resin is an excellent candidate for wide variety of electronics, consumer, and industrial applications that require a balance of scratch resistance and ductility.

| GENERAL INFORMATION | |
|-----------------------|--|
| Features | Scratch Resistance, Impact resistant, Weatherable/UV stable, No PFAS intentionally added |
| Polymer Types | Polycarbonate (PC) |
| Processing Techniques | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|----------------------------|---|
| Automotive | Automotive Interiors |
| Consumer | Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance |
| Electrical and Electronics | Electrical Devices and Displays, Electrical Components and Infrastructure |

TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, yield, 50 mm/min | 61 | MPa | ISO 527 |
| Tensile Stress, break, 50 mm/min | 54 | MPa | ISO 527 |
| Tensile Strain, yield, 50 mm/min | 7 | % | ISO 527 |
| Tensile Strain, break, 50 mm/min | 88 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 2084 | MPa | ISO 527 |
| Flexural Modulus, 2 mm/min | 2151 | MPa | ISO 178 |
| Flexural Stress, yield, 2 mm/min | 91 | MPa | ISO 178 |
| Tensile Modulus, 50 mm/min | 2268 | MPa | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | 65 | % | ASTM D638 |
| Tensile Strain, yld, Type I, 50 mm/min | 7 | % | ASTM D638 |
| Tensile Stress, brk, Type I, 50 mm/min | 52 | MPa | ASTM D638 |
| Tensile Stress, yld, Type I, 50 mm/min | 62 | MPa | ASTM D638 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2130 | MPa | ASTM D790 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 88 | MPa | ASTM D790 |
| Pencil Hardness test, 0.5 kgf | F | - | ASTM D3363 |
| Hardness, Rockwell M | 66 | - | ASTM D785 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, notched 80*10*3 +23°C | 45 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*3 -30°C | 45 | kJ/m ² | ISO 180/1A |
| Izod Impact, unnotched 80*10*3 +23°C | 183 | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*3 -30°C | 173 | kJ/m ² | ISO 180/1U |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm | 27 | kJ/m ² | ISO 179/1eA |
| Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm | 3 | kJ/m ² | ISO 179/1eA |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------------|--------------|
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm | 270 | kJ/m ² | ISO 179/1eU |
| Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm | 275 | kJ/m ² | ISO 179/1eU |
| Izod Impact, notched, 23°C | 300 | J/m | ASTM D256 |
| Izod Impact, notched, 0°C | 140 | J/m | ASTM D256 |
| Izod Impact, notched, -30°C | 82 | J/m | ASTM D256 |
| Izod Impact, unnotched, 23°C | NB | J/m | ASTM D4812 |
| Izod Impact, unnotched, -30°C | 1730 | J/m | ASTM D4812 |
| Instrumented Dart Impact Total Energy, 23°C | 66 | J | ASTM D3763 |
| THERMAL ⁽¹⁾ | | | |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 113 | °C | ISO 75/Af |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 129 | °C | ISO 75/Bf |
| HDT, 1.82 MPa, 3.2mm, unannealed | 114 | °C | ASTM D648 |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 129 | °C | ASTM D648 |
| Vicat Softening Temp, Rate B/50 | 134 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 137 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/50 | 134 | °C | ASTM D1525 |
| Vicat Softening Temp, Rate B/120 | 136 | °C | ASTM D1525 |
| CTE, -40°C to 40°C, flow | 7.2E-05 | 1/°C | ISO 11359-2 |
| CTE, -40°C to 40°C, xflow | 8.1E-05 | 1/°C | ISO 11359-2 |
| CTE, -40°C to 40°C, flow | 7.2E-05 | 1/°C | ASTM E831 |
| CTE, -40°C to 40°C, xflow | 8.1E-05 | 1/°C | ASTM E831 |
| PHYSICAL ⁽¹⁾ | | | |
| Density | 1.18 | g/cm ³ | ISO 1183 |
| Moisture Absorption, (23°C/50% RH/24 hrs) | 0.04 | % | ASTM D570 |
| Water Absorption, (23°C/24hrs) | 0.08 | % | ASTM D570 |
| Specific Gravity | 1.18 | - | ASTM D792 |
| Mold Shrinkage, flow, 24 hrs ⁽²⁾ | 0.5 – 0.8 | % | ASTM D955 |
| Mold Shrinkage, xflow, 24 hrs ⁽²⁾ | 0.5 – 0.8 | % | ASTM D955 |
| Melt Volume Rate, MVR at 300°C/ 1.2 kg | 9 | cm ³ /10 min | ISO 1133 |
| Melt Flow Rate, 300°C/1.2 kgf | 10 | g/10 min | ASTM D1238 |
| Melt Volume Rate, MVR at 300°C/ 1.2 kg | 9 | cm ³ /10 min | ASTM D1238 |
| INJECTION MOLDING ⁽³⁾ | | | |
| Drying Temperature | 110 | °C | |
| Drying Time | 3 – 4 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 290 – 310 | °C | |
| Rear - Zone 1 Temperature | 260 – 280 | °C | |
| Middle - Zone 2 Temperature | 280 – 305 | °C | |
| Front - Zone 3 Temperature | 290 – 310 | °C | |
| Nozzle Temperature | 290 – 310 | °C | |
| Mold Temperature | 60 – 85 | °C | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.