# FLEX NORYL™ RESIN WCA901

REGION ASIA

## DESCRIPTION

FLEX NORYL WCA901 resin is a flexible, non-reinforced extrudable blend of Polyphenylene Ether (PPE) + Thermoplastic Elastomer (TPE). This material contains non-halogenated flame retardant and performance capable of meeting UL VW-1 requirements, 105C end use temperature rating, and heat deformation performance as defined by UL 1581. FLEX NORYL WCA901 resin is intended for evaluation in wire and cable applications. It has a Shore A Hardness reading of 91 and exhibits superior thermal stability, very low water absorption, good electric properties, and low specific gravity. Processing is typically conducted on standard extrusion equipment, and UL 1581 testing is conducted on 2.0mm wire with 0.12mm X 20 stranded copper conductor.

| GENERAL INFORMATION | |
|---|---|
| **Features** | Flame Retardant, Good Processability, Hydrolytic Stability, Low Warpage, Flexible, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Creep resistant, Dimensional stability |
| **Fillers** | Unreinforced |
| **Polymer Types** | Polyphenylene Ether + TPE (PPE+TPE) |
| **Processing Techniques** | Wire Coating Extrusion |

| INDUSTRY | SUB INDUSTRY |
|---|---|
| Electrical and Electronics | Mobile Phone - Computer - Tablets |
| Industrial | Electrical |

## TYPICAL PROPERTY VALUES

Revision 20260717

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| **MECHANICAL** [1] | | | |
| **Tensile Stress, brk, Type I, 50 mm/min** | 23 | MPa | ASTM D638 |
| **Tensile Strain, brk, Type I, 50 mm/min** | 110 | % | ASTM D638 |
| **Flexural Modulus** | | | |
| 12.5 mm/min, 100 mm span | 390 | MPa | ASTM D790 |
| 12.5 mm/min | 390 | MPa | ISO 178 |
| **Hardness, Shore A, 30S reading** | 91 | - | ASTM D2240 |
| **Tensile Stress, break, 50 mm/min** | 22 | MPa | ISO 527 |
| **Tensile Strain, break, 50 mm/min** | 95 | % | ISO 527 |
| **Tear strength** | 13 | N/mm | ISO 6383 |
| **IMPACT** [1] | | | |
| **Brittleness Temperature** | <-40 | °C | ASTM D746 |
| **PHYSICAL** [1] | | | |
| **Specific Gravity** | 1.1 | - | ASTM D792 |
| **Melt Flow Rate, 250°C/10.0 kgf** | 10 | g/10 min | ASTM D1238 |
| **ELECTRICAL** [1] | | | |
| **Volume Resistivity** | 5.1E+15 | Ω.cm | ASTM D257 |
| **Surface Resistivity** | 4.2E+16 | Ω | ASTM D257 |
| **Relative Permittivity, 1 MHz** | 2.7 | - | IEC 60250 |
| **Dissipation Factor, 1 MHz** | 0.004 | - | IEC 60250 |

© 2026 Copyright by SABIC. All rights reserved

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| Comparative Tracking Index [2] | 600 | V | IEC 60112 |
| FLAME CHARACTERISTICS [3] | | | |
| UL Yellow Card Link | E207780-100035708 | - | - |
| UL Recognized, 94V-0 Flame Class Rating | ≥6 | mm | UL 94 |
| Oxygen Index (LOI) | 27 | % | ISO 4589 |
| WIRE AND CABLE - UL 1581 TESTED ON 2.0MM WIRE WITH 0.12MMX20 STRANDED COPPER | | | |
| Tensile strength @ break | 26 | MPa | UL 1581 |
| Tensile elongation @ break | 190 | % | UL 1581 |
| Tensile strength @ break after 7days @136°C | 27 | MPa | UL 1581 |
| Tensile elongation @ break after 7days @136°C | 127 | % | UL 1581 |
| UL temperature rating | 105 | °C | UL 1581 |
| Heat Deformation at 121°C/250g | 15 | % | UL 1581 |
| VW-1 | Pass | - | UL 1581 |
| WIRE COATING EXTRUSION | | | |
| Drying Temperature | 75 – 85 | °C | |
| Drying Time | 5 – 7 | Hrs | |
| Drying Time (Cumulative) | 12 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Extruder Length/Diameter Ratio (L/D) | 22:1 to 26:1 | - | |
| Screw Speed | 15 – 85 | rpm | |
| Feed Zone Temperature | 200 – 240 | °C | |
| Middle Zone Temperatures | 240 – 270 | °C | |
| Head Zone Temperature | 240 – 270 | °C | |
| Neck Temperature | 240 – 270 | °C | |
| Cross-head Temperature | 240 – 270 | °C | |
| Die Temperature | 240 – 270 | °C | |
| Melt Temperature | 240 – 270 | °C | |
| Conductor Pre-heat Temperature | 80 – 150 | °C | |
| Screen Pack | 150 – 100 | - | |
| Cooling Water Air Gap | 100 – 200 | mm | |
| Water Bath Temperature | 15 – 45 | °C | |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Value shown here is based on internal measurement.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved