

SILTEM™ RESIN STM1700

REGION AMERICAS

DESCRIPTION

SILTEM™ STM1700 resin is a medium flexible polyetherimide(PEI)-siloxane copolymer designed for wire and cable applications. The material is RoHS compliant and offers a halogen free (according VDE 0472) flame retardant solution that also offers low smoke emission and toxicity. It is an amber colored transparent material that can be selfcolored and easily processed on conventional processing equipment. The material may also be used for extrusion of e.g. corrugated pipes and profiles as well as flexible injection molded parts.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

INDUSTRY	SUB INDUSTRY
Automotive	Aerospace
Electrical and Electronics	Energy Management
Industrial	Electrical, Material Handling, Defense
Mass Transportation	Rail

TYPICAL PROPERTY VALUES

Revision 20231113

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	53	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	20	%	ASTM D638
Tensile Modulus, 5 mm/min	2400	MPa	ASTM D638
Flexural Stress	94	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	94	MPa	ASTM D790
Flexural Modulus	2150	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2150	MPa	ASTM D790
Hardness, Shore D	80	-	ASTM D2240
Taber Abrasion, CS-17, 1 kg	50	mg/1000cy	ASTM D1044
Tensile Stress, yield, 50 mm/min	68	MPa	ISO 527
Tensile Stress, break, 50 mm/min	59	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	15	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	98	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
Tear Strength @ 1.6mm	37	N/mm	ISO 34 (Method A)
IMPACT			
Izod Impact, notched, 23°C	175	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	16	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	145	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/120	180	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	164	°C	ISO 75/Bf
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.87 – 0.92	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	7	g/10 min	ASTM D1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.76	%	ISO 62-1
Matrix Tg	200	°C	DMA
ELECTRICAL			
Volume Resistivity	>1.E+16	Ω.cm	ASTM D257
Surface Resistivity	>1.E+15	Ω	ASTM D257
Dielectric Strength, in oil, 3.2 mm	16.7	kV/mm	ASTM D149
Relative Permittivity, 100 Hz	3.13	-	ASTM D150
Relative Permittivity, 100 kHz	3	-	ASTM D150
Relative Permittivity, 1 MHz	3.04	-	ASTM D150
Dissipation Factor, 100 Hz	0.011	-	ASTM D150
Dissipation Factor, 100 kHz	0.0061	-	ASTM D150
Dissipation Factor, 1 MHz	0.0054	-	ASTM D150
Comparative Tracking Index	175	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Oxygen Index (LOI)	48	%	ASTM D2863
INJECTION MOLDING			
Drying Temperature	105	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	320 – 330	°C	
Nozzle Temperature	320 – 330	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	320 – 330	°C	
Mold Temperature	110 – 120	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	
WIRE COATING EXTRUSION			
Drying Temperature	110 – 130	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Extruder Length/Diameter Ratio (L/D)	22:1 to 28:1	-	
Compression Ratio	2.1:1 to 2.7:1	-	
Feed - Compression - Metering	10 - 5 - 10	D	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	5 – 50	rpm	
Feed Zone Temperature	310 – 340	°C	
Middle Zone Temperatures	320 – 350	°C	
Head Zone Temperature	330 – 360	°C	
Neck Temperature	330 – 360	°C	
Cross-head Temperature	330 – 360	°C	
Die Temperature	330 – 360	°C	
Melt Temperature	330 – 360	°C	
Conductor Pre-heat Temperature	100 – 150	°C	
Screen Pack	100 – 200	-	
Water Bath Temperature	70 – 90	°C	

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.