

# LEXANT™ VISUALFX™ RESIN FXM121R

REGION AMERICAS

## DESCRIPTION

PC in special effects colors. Metallic and pearlescent additives. Color package may affect performance.

## TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES  | TYPICAL VALUES                 | UNITS    | TEST METHODS |
|---|--------------------------------|----------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>                    |                                |          |              |
| Tensile Stress, yld, Type I, 50 mm/min              | 61                             | MPa      | ASTM D638    |
| Tensile Stress, brk, Type I, 50 mm/min              | 57                             | MPa      | ASTM D638    |
| Tensile Strain, yld, Type I, 50 mm/min              | 6.2                            | %        | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min              | 90                             | %        | ASTM D638    |
| Tensile Modulus, 50 mm/min                          | 2340                           | MPa      | ASTM D638    |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span        | 93                             | MPa      | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span            | 2370                           | MPa      | ASTM D790    |
| <b>IMPACT <sup>(1)</sup></b>                        |                                |          |              |
| Izod Impact, notched, 23°C                          | 106                            | J/m      | ASTM D256    |
| Instrumented Dart Impact Total Energy, 23°C         | 48                             | J        | ASTM D3763   |
| <b>THERMAL <sup>(1)</sup></b>                       |                                |          |              |
| HDT, 0.45 MPa, 3.2 mm, unannealed                   | 135                            | °C       | ASTM D648    |
| HDT, 1.82 MPa, 3.2mm, unannealed                    | 123                            | °C       | ASTM D648    |
| Relative Temp Index, Elec <sup>(2)</sup>            | 130                            | °C       | UL 746B      |
| Relative Temp Index, Mech w/impact <sup>(2)</sup>   | 130                            | °C       | UL 746B      |
| Relative Temp Index, Mech w/o impact <sup>(2)</sup> | 130                            | °C       | UL 746B      |
| <b>PHYSICAL <sup>(1)</sup></b>                      |                                |          |              |
| Specific Gravity                                    | 1.2                            | -        | ASTM D792    |
| Mold Shrinkage, flow, 3.2 mm <sup>(3)</sup>         | 0.5 – 0.7                      | %        | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf                       | 18.2                           | g/10 min | ASTM D1238   |
| <b>ELECTRICAL <sup>(1)</sup></b>                    |                                |          |              |
| Comparative Tracking Index (UL) {PLC}               | 3                              | PLC Code | UL 746A      |
| Hot-Wire Ignition (HWI), PLC 2                      | ≥1.5                           | mm       | UL 746A      |
| Hot-Wire Ignition (HWI), PLC 3                      | ≥1.1                           | mm       | UL 746A      |
| High Amp Arc Ignition (HAI), PLC 0                  | ≥1.5                           | mm       | UL 746A      |
| High Amp Arc Ignition (HAI), PLC 1                  | ≥3                             | mm       | UL 746A      |
| High Amp Arc Ignition (HAI), PLC 2                  | ≥1.1                           | mm       | UL 746A      |
| High Voltage Arc Track Rate {PLC}                   | 2                              | PLC Code | UL 746A      |
| <b>FLAME CHARACTERISTICS <sup>(2)</sup></b>         |                                |          |              |
| UL Yellow Card Link                                 | <a href="#">E121562-220943</a> | -        | -            |
| UV-light, water exposure/immersion                  | F2                             | -        | UL 746C      |
| UL Recognized, 94HB Flame Class Rating              | ≥0.7                           | mm       | UL 94        |
| <b>INJECTION MOLDING <sup>(4)</sup></b>             |                                |          |              |
| Drying Temperature                                  | 120                            | °C       |              |

| PROPERTIES                  | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Drying Time                 | 3 – 4          | Hrs   |              |
| Drying Time (Cumulative)    | 48             | Hrs   |              |
| Maximum Moisture Content    | 0.02           | %     |              |
| Melt Temperature            | 280 – 305      | °C    |              |
| Nozzle Temperature          | 275 – 300      | °C    |              |
| Front - Zone 3 Temperature  | 280 – 305      | °C    |              |
| Middle - Zone 2 Temperature | 270 – 295      | °C    |              |
| Rear - Zone 1 Temperature   | 260 – 280      | °C    |              |
| Mold Temperature            | 70 – 95        | °C    |              |
| Back Pressure               | 0.3 – 0.7      | MPa   |              |
| Screw Speed                 | 40 – 70        | rpm   |              |
| Shot to Cylinder Size       | 40 – 60        | %     |              |
| Vent Depth                  | 0.025 – 0.076  | mm    |              |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.