LNP™ STAT-KON™ COMPOUND EJL20C

DESCRIPTION

LNP STAT-KON EJL20C is a static dissipative and wear resistant compound based on Polyetherimide (PEI) resin containing carbon nanotubes and PTFE. Added features of this grade include: LNP Clean Compounding Technology, Dimensional Stability, Wear Resistance. This material has a fit in broad range of markets including the semiconductor industry.

GENERAL INFORMATION	
Features	Electrically Conductive, Wear resistant, Low ionics/Outgassing/Liquid particle count, Dimensional stability
Fillers	Carbon nanotube, PTFE
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding
Regional Availability	Europe, Asia, Americas

TYPICAL PROPERTY VALUES

Revision 20260326

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, brk, Type I, 50 mm/min	98	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	5	%	ASTM D638
Tensile Modulus, 50 mm/min	2900	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	140	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3100	MPa	ASTM D790
Tensile Stress, break, 50 mm/min	103	MPa	ISO 527
Tensile Strain, break, 50 mm/min	7	%	ISO 527
Tensile Modulus, 1 mm/min	3660	MPa	ISO 527
Flexural Strength, 2 mm/min	146	MPa	ISO 178
Flexural Modulus, 2 mm/min	3260	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched, 23°C	48	J/m	ASTM D256
Izod Impact, unnotched, 23°C	610	J/m	ASTM D4812
Izod Impact, notched 80*10*3 +23°C	6	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80*10*3 +23°C	48	kJ/m²	ISO 180/1U
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	210	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	200	°C	ASTM D648
PHYSICAL [1]			
Specific Gravity	1.34	-	ASTM D792
Melt Volume Rate			
337°C/6.7 kg	3	cm³/10 min	ISO 1133
ELECTRICAL [1]			
Surface Resistivity	1.E+04 – 1.E+07	Ω	ASTM D257
INJECTION MOLDING [2]			
Drying Temperature	150	°C	

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	340 – 400	°C	
Nozzle Temperature	380 – 400	°C	
Front - Zone 3 Temperature	360 – 400	°C	
Middle - Zone 2 Temperature	350 – 390	°C	
Rear - Zone 1 Temperature	340 – 380	°C	
Mold Temperature	140 – 180	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	1.5 – 2	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved