

NORYL™ PPE POWDERS + CONCENTRATES 630

REGION EUROPE

DESCRIPTION

NORYL PPE 630 powder is a medium molecular weight polymer based on Polyphenylene Ether (PPE). This material is intended for use as an additive or a building block in a variety of thermoplastics and thermoplastic elastomers such as Styrenic Block Copolymers. PPE 640 powder can be used to improve properties (i.e. Heat Distortion and Creep Resistance). It is hydrolytically stable and non-hydroscopic (typically less than 0.2% water uptake). The powder is soluble in common organic solvents like toluene, chloroform, and THF. Chemical name: Poly (2,6-dimethyl-, 1,4-phenylene ether) (PPE) Formula: (C₈H₈O)_n Regulatory Status: Complies with the FDA regulation 21CFR 177.2460. Also complies with EU Directive 2002/72/EC.

GENERAL INFORMATION	
Features	Flame Retardant, Hydrolytic Stability, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Creep resistant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene ether (PPE)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Mobile Phone - Computer - Tablets, Circuit Boards/Additives
Industrial	Industrial General
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20241009

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL ⁽¹⁾			
Tg (half width)	214	°C	SABIC method
PHYSICAL ⁽¹⁾			
Mean Resin Particle Size	190	micrometer	SABIC method
Physical Form	POWDER	-	SABIC method
Bulk Density	462	kg/m ³	ISO 1183
Intrinsic Viscosity	0.33	dl/g	SABIC method
Phenolic End-group Content	1180	ppm	SABIC method
Mw	47600	-	SABIC method
Mn	17300	-	SABIC method
D	2.8	-	SABIC method
Toluene Content	<1500	ppm	SABIC method

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.