

# LNPTM STAT-KONTM COMPOUND RE002

RC-1002

## DESCRIPTION

LNP STAT-KON RE002 compound is based on Nylon 6/6 resin containing 10% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	134	MPa	ASTM D638
Tensile Stress, break	126	MPa	ASTM D638
Tensile Strain, yield	2.3	%	ASTM D638
Tensile Strain, break	2.3	%	ASTM D638
Tensile Modulus, 50 mm/min	8270	MPa	ASTM D638
Flexural Stress	206	MPa	ASTM D790
Flexural Modulus	6890	MPa	ASTM D790
Tensile Stress, yield	131	MPa	ISO 527
Tensile Stress, break	131	MPa	ISO 527
Tensile Strain, yield	2.1	%	ISO 527
Tensile Strain, break	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	7800	MPa	ISO 527
Flexural Stress	191	MPa	ISO 178
Flexural Modulus	6000	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	363	J/m	ASTM D4812
Izod Impact, notched, 23°C	26	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	5	J	ASTM D3763
Multiaxial Impact	1	J	ISO 6603
Izod Impact, unnotched 80°10°4 +23°C	24	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	3	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	258	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	245	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.88E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.28E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	2.90E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.30E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	254	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	241	°C	ISO 75/Af
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.18	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.8	%	ASTM D570
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.6 – 0.8	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1 – 3	%	ASTM D955
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.74	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.3	%	ISO 294
Density	1.18	g/cm <sup>3</sup>	ISO 1183
<b>ELECTRICAL <sup>(1)</sup></b>			
Surface Resistivity <sup>(3)</sup>	1.E+01 – 1.E+03	Ω	ASTM D257
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.