

# LEXANT™ FR RESIN LGK4030

## DESCRIPTION

LGK4030 is based on Polycarbonate containing 40% of glass fiber and glass flakes. Added feature includes Dimensional Stability and Flame Retardant.

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	129	MPa	SABIC - Japan Method
Tensile Strain, break	3 – 5	%	SABIC - Japan Method
Flexural Stress	180	MPa	ASTM D790
Flexural Modulus	8820	MPa	ASTM D790
Hardness, Rockwell M	91	-	ASTM D785
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	107	J/m	ASTM D256
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	145	°C	ASTM D648
CTE, -30°C to 30°C	0.000022 – 0.000043	1 / °C	TMA
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.54	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.14	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.15 – 0.2	%	SABIC method
<b>ELECTRICAL <sup>(1)</sup></b>			
Surface Resistivity	1.E+16	Ω	ASTM D257
<b>FLAME CHARACTERISTICS <sup>(3)</sup></b>			
UL Yellow Card Link	<a href="#">E45587-236911</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.5	mm	UL 94

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.