LNP™ THERMOCOMP™ COMPOUND QC006

QC-1006
REGION EUROPE

DESCRIPTION

LNP THERMOCOMP QC006 compound is based on Nylon 6/10 resin containing 30% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polyamide 610 (Nylon 610)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break, 5 mm/min	196	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.7	%	ISO 527
Tensile Modulus, 1 mm/min	18700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	290	MPa	ISO 178
Flexural Stress, break, 2 mm/min	280	MPa	ISO 178
Flexural Modulus, 2 mm/min	15200	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched 80*10*4 +23°C	62	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	15	kJ/m²	ISO 180/1A
THERMAL [1]			
CTE, 23°C to 60°C, flow	7.4E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.5E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	221	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	205	°C	ISO 75/Af
PHYSICAL [1]			
Mold Shrinkage, flow [2]	0.1 – 0.3	%	SABIC method
Density	1.22	g/cm³	ISO 1183
Water Absorption, (23°C/24hrs)	0.25	%	ISO 62-1
ELECTRICAL [1]			

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Surface Resistivity	1.E+01 – 1.E+03	Ω	ASTM D257
INJECTION MOLDING [3]			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved