

# ULTEM™ RESIN 2100F

REGION ASIA

## DESCRIPTION

10% Glass fiber filled, standard flow Polyetherimide (Tg 217°C). ECO Conforming, UL94 V0 and 5VA listing. NSF 51 listing. WRAS certification in recognized colors.

This material is food contact compliant in most jurisdictions – exceptions may exist, request a declaration for details.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Smoke and Toxicity, Amorphous, Low Shrinkage, Sustainable (bio-based offerings), Food contact, Non halogenated flame retardant, Electroplatable, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles
Building and Construction	Building Component, Water Management
Consumer	Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture
Electrical and Electronics	Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication
Hygiene and Healthcare	Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial	Electrical, Material Handling, Textile, Eyewear
Mass Transportation	Rail
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20250404

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	114	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	6	%	ASTM D638
Tensile Modulus, 5 mm/min	4680	MPa	ASTM D638
Flexural Stress, brk, 2.6 mm/min, 100 mm span	199	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	5170	MPa	ASTM D790
Hardness, Rockwell M	114	-	ASTM D785
IMPACT			
Izod Impact, unnotched, 23°C	480	J/m	ASTM D4812
Izod Impact, notched, 23°C	53	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	459	J/m	ASTM D256
THERMAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	223	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	208	°C	ASTM D648
CTE, -20°C to 150°C, flow	3.0E-05	1/°C	ASTM E831
Relative Temp Index, Elec <sup>(1)</sup>	170	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	170	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	170	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.21	%	ASTM D570
Water Absorption, (23°C/Saturated)	1.2	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.6	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	7	g/10 min	ASTM D1238
ELECTRICAL			
Volume Resistivity	1.E+17	Ω.cm	ASTM D257
Dielectric Strength, in oil, 1.6 mm	27.6	kV/mm	ASTM D149
Relative Permittivity, 1 kHz	3.5	-	ASTM D150
Dissipation Factor, 1 kHz	0.0014	-	ASTM D150
Dissipation Factor, 2450 MHz	0.0046	-	ASTM D150
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
FLAME CHARACTERISTICS <sup>(1)</sup>			
UL Yellow Card Link	<a href="#">E121562-502535</a>	-	-
UL Yellow Card Link 2	<a href="#">E121562-102518191</a>	-	-
UL Recognized, 94-5VA Flame Class Rating	≥1.9	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.41	mm	UL 94
Oxygen Index (LOI)	47	%	ASTM D2863
NBS Smoke Density, Flaming, Ds 4 min	1.8	-	ASTM E662
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.