

LNPTM ELCRINTM CX7240BL

DESCRIPTION

LNP ELCRIN CX7240BL Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend is an injection moldable, medium flow, non chlorinated/brominated flame retardant grade with incorporation of renewable PC feedstock. It has a UL94 V0@0.75mm, 5VA@3.0mm and 5VB@1.5mm flame rating and contains up to 23% renewable content. Renewable content certified by ISCC+ mass balance methodology. This grade has improved weld line strength and chemical resistance compared to standard PC/ABS blends and is a good candidate for thin wall applications. This grade also has good processability with opportunities for shorter injection molded cycle times compared to standard PC/ABS. ELCRIN CX7240BL is a product available in wide range of opaque colors and may be an excellent candidate for a variety of electronics applications such as mobile phones, tablets, audio equipment, gaming devices, thin wall industrial housings, and electric vehicle battery and energy storage equipment.

GENERAL INFORMATION	
Features	Chemical Resistance, Good Processability, Thin Wall, Amorphous, Sustainable (bio-based offerings), Non Cl/Br flame retardant, Enhanced mold release, Dimensional stability, Impact resistant
Fillers	Unreinforced
Polymer Types	Polycarbonate + ABS (PC+ABS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive EV Batteries, Aerospace, Recreational/Specialty Vehicles
Building and Construction	Building Component, Water Management
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Hydrocarbon and Energy	Energy Storage
Hygiene and Healthcare	General Healthcare
Industrial	Electrical, Industrial General
Mass Transportation	Rail

TYPICAL PROPERTY VALUES

Revision 20250508

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	58	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4.1	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 5 mm/min	2600	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	104	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2500	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	90	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Strength, 2 mm/min	96	MPa	ISO 178

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	700	J/m	ASTM D256
Izod Impact, notched, -30°C	175	J/m	ASTM D256
Izod Impact, notched 80*10*3 +23°C	20	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	20	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	22	kJ/m ²	ISO 179/1eA
Instrumented Dart Impact Total Energy, 23°C	65	J	ASTM D3763
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	100	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	89	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	99	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	93	°C	ISO 75/Af
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	110	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	110	°C	ISO 306
Vicat Softening Temp, Rate B/120	113	°C	ISO 306
Relative Temp Index, Elec ⁽²⁾	90	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	90	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	90	°C	UL 746B
Ball Pressure Test, 75°C +/- 2°C	Pass	-	IEC 60695-10-2
Thermal Conductivity	0.2	W/m.°C	ISO 8302
PHYSICAL ⁽¹⁾			
Specific Gravity	1.19	-	ASTM D792
Density	1.2	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Water Absorption, (23°C/saturated)	0.2	%	ISO 62-1
Melt Flow Rate, 260°C/2.16 kgf	18	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 260°C/2.16 kg	15	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.4 – 0.6	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Comparative Tracking Index (UL) {PLC} ⁽²⁾	3	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1 ⁽²⁾	≥3	mm	UL 746A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hot-Wire Ignition (HWI), PLC 3 ⁽²⁾	≥0.75	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0 ⁽²⁾	≥0.75	mm	UL 746A
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link ⁽²⁾	E207780-101674340	-	-
UL Yellow Card Link 2 ⁽²⁾	E207780-474277	-	-
UL Recognized, 94-5VA Flame Class Rating ⁽²⁾	≥3.0	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating ⁽²⁾	≥1.5	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating ⁽²⁾	≥0.75	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating ⁽²⁾	≥0.6	mm	UL 94
UL Recognized, 94V-2 Flame Class Rating ⁽²⁾	≥0.4	mm	UL 94
Glow Wire Flammability Index, 0.75 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at, by VDE	0.75	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 0.75 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 0.75 mm, by VDE	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm, by VDE	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm, by VDE	775	°C	IEC 60695-2-13
UV-light, water exposure/immersion ⁽²⁾	F2	-	UL 746C
Oxygen Index (LOI)	34	%	ISO 4589
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 300	°C	
Nozzle Temperature	250 – 300	°C	
Front - Zone 3 Temperature	250 – 300	°C	
Middle - Zone 2 Temperature	240 – 290	°C	
Rear - Zone 1 Temperature	230 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 85	°C	
Vent Depth	0.03 – 0.075	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.