

LNPTTM LUBRICOMPTM COMPOUND RFL36SXC

RFL-4036

DESCRIPTION

LNP LUBRICOMP RFL36SXC compound is based on Nylon 6/6 resin containing 30% glass fiber, 15% PTFE. Added features of this grade include: Heat Stabilized, Wear Resistant.

GENERAL INFORMATION	
Features	Heat Stabilized, Wear resistant
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	173	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	9700	MPa	ISO 527
Flexural Stress, break, 2 mm/min	238	MPa	ISO 178
Flexural Modulus, 2 mm/min	7900	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	261	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	249	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage on Tensile Bar, flow ⁽²⁾	0.2 – 0.4	%	SABIC method
Density	1.49	g/cm ³	ISO 1183
INJECTION MOLDING ⁽³⁾			
Drying Time	4	Hrs	
Drying Temperature	80	°C	
Melt Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Middle - Zone 2 Temperature	280 – 295	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	295 – 305	°C	
Maximum Moisture Content	0.15 – 0.25	%	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	
Mold Temperature	95 – 110	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.