

# LNPTM STAT-KONTM COMPOUND EE003XXC

EC-1003 CCS

## DESCRIPTION

LNP STAT-KON EE003XXC compound is based on Polyetherimide (PEI) resin containing 15% carbon fiber. Added features of this grade include: LNP Clean Compounding Technology, Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Low ionics/Outgassing/Liquid particle count, Carbon fiber filled, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

## TYPICAL PROPERTY VALUES

Revision 20241028

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break	165	MPa	ASTM D638
Tensile Strain, break	1.6	%	ASTM D638
Flexural Stress	248	MPa	ASTM D790
Flexural Modulus	11720	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	373	J/m	ASTM D4812
<b>THERMAL <sup>(1)</sup></b>			
Relative Temp Index, Elec <sup>(2)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	105	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.33	g/cm <sup>3</sup>	ASTM D792
Mold Shrinkage, flow, 24 hrs <sup>(3)</sup>	0.1 – 0.3	%	ASTM D955
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity <sup>(4)</sup>	1.E+02 – 1.E+06	Ω.cm	ASTM D257
Surface Resistivity <sup>(4)</sup>	1.E+02 – 1.E+06	Ω	ASTM D257
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-101282750</a>	-	-
UL Yellow Card Link 2	<a href="#">E207780-101345232</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.75	mm	UL 94

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Extended Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 400	°C	
Rear - Zone 1 Temperature	360 – 380	°C	
Middle - Zone 2 Temperature	370 – 390	°C	
Front - Zone 3 Temperature	380 – 400	°C	
Nozzle Temperature	390 – 400	°C	
Mold Temperature	140 – 180	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw speed (Circumferential speed)	0.2 – 0.3	m/s	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Measurement meets requirements as specified in ASTM D4496.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.