

# LEXAN™ FR RESIN SLD3000

## DESCRIPTION

Antistatic colorable/opaque FR PC grade

GENERAL INFORMATION	
Features	Flame Retardant, Antistatic, Transparent/Translucent, Non Cl/Br flame retardant
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield, 50 mm/min	52	MPa	ASTM D638
Flexural Stress, yield, 6.4 mm	80	MPa	ASTM D790
Flexural Modulus	2030	MPa	ASTM D790
Tensile Strain, break, 50 mm/min	200	%	ISO 527
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	700	J/m	ASTM D256
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	100	°C	ASTM D648
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.21	-	ASTM D792
Mold Shrinkage, flow, 1.5-3.2 mm <sup>(2)</sup>	0.4	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm <sup>(2)</sup>	0.5	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	19	g/10 min	ASTM D1238
<b>ELECTRICAL <sup>(1)</sup></b>			
Surface Resistivity <sup>(3)</sup>	1.2E+12	Ω	ASTM D257
<b>FLAME CHARACTERISTICS <sup>(4)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-228454</a>	-	-
UL Recognized, 94V-2 Flame Class Rating	≥1	mm	UL 94
UL Recognized, 94HB Flame Class Rating	≥0.5	mm	UL 94
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Drying Temperature	90 – 100	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.04	%	
Melt Temperature	240 – 260	°C	
Nozzle Temperature	230 – 260	°C	
Front - Zone 3 Temperature	230 – 260	°C	
Middle - Zone 2 Temperature	220 – 255	°C	
Rear - Zone 1 Temperature	220 – 245	°C	
Mold Temperature	30 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.38 – 0.76	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Measurement meets requirements as specified in ASTM D4496.
- (4) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.