

# ULTEM™ RESIN AUT200G6

## DESCRIPTION

30% Glass fiber filled, enhanced flow Polyetherimide (Tg 217C).

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 5 mm/min	168	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	158	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Tensile Modulus, 5 mm/min	9230	MPa	ASTM D638
Flexural Stress, brk, 2.6 mm/min, 100 mm span	220	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	9230	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	20	mg/1000cy	SABIC method
Tensile Stress, break, 5 mm/min	165	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	9500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	225	MPa	ISO 178
Flexural Modulus, 2 mm/min	8500	MPa	ISO 178
Ball Indentation Hardness, H358/30	165	MPa	ISO 2039-1
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	85	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	437	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	40	kJ/m <sup>2</sup>	ISO 180/1U
Charpy Impact, notched, 23°C	10	kJ/m <sup>2</sup>	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
CTE, -20°C to 150°C, flow	1.62E-05	1/°C	ASTM E831
CTE, -20°C to 150°C, xflow	4.14E-05	1/°C	ASTM E831
Thermal Conductivity	0.33	W/m·°C	ISO 8302
CTE, -40°C to 150°C, flow	1.7E-05	1/°C	ISO 11359-2
CTE, -40°C to 150°C, xflow	4.9E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	225	°C	ISO 306
Vicat Softening Temp, Rate B/50	213	°C	ISO 306
Vicat Softening Temp, Rate B/120	220	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	215	°C	ISO 75/Be

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	180	°C	ISO 75/Ae
Relative Temp Index, Mech w/impact <sup>(2)</sup>	170	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	180	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.51	-	ASTM D792
Melt Flow Rate, 337°C/6.6 kgf	7.6	g/10 min	ASTM D1238
Mold Shrinkage on Tensile Bar, flow <sup>(3)</sup>	0.2 – 0.4	%	SABIC method
Density	1.51	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.9	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.5	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	8	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0016	-	IEC 60250
Dissipation Factor, 1 MHz	0.0023	-	IEC 60250
Comparative Tracking Index <sup>(4)</sup>	150	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.5	-	IEC 60250
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	370 – 410	°C	
Nozzle Temperature	360 – 410	°C	
Front - Zone 3 Temperature	370 – 420	°C	
Middle - Zone 2 Temperature	360 – 410	°C	
Rear - Zone 1 Temperature	350 – 400	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	140 – 180	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) RTI for this grade is not measured and is based on grades with similar formulation and performance.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Value shown here is based on internal measurement.

(5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.