

ULTEM™ RESIN 2212R

REGION AMERICAS

DESCRIPTION

20% Milled glass filled, enhanced flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming, UL94 V0 and 5VA listing.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

INDUSTRY	SUB INDUSTRY		
Automotive	Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles		
Building and Construction	Building Component, Water Management		
Consumer	Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture		
Electrical and Electronics	Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication		
Hygiene and Healthcare	Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing		
Industrial	Electrical, Material Handling, Textile, Eyewear		
Mass Transportation	Rail		
Packaging	Industrial Packaging		

TYPICAL PROPERTY VALUES

PROPERTIES TYPICAL VALUES UNITS TEST METHODS MECHANICAL ASTM D638 Tensile Stress, brk, Type I, 5 mm/min 92 MPa Tensile Strain, brk, Type I, 5 mm/min 6 % ASTM D638 4270 MPa Tensile Modulus, 5 mm/min ASTM D638 Flexural Stress, brk, 2.6 mm/min, 100 mm span 172 MPa ASTM D790 Flexural Modulus, 2.6 mm/min, 100 mm span 5100 MPa ASTM D790 IMPACT Izod Impact, notched, 23°C 48 ASTM D256 J/m Izod Impact, Reverse Notched, 3.2 mm 384 J/m ASTM D256 THERMAL HDT, 1.82 MPa, 6.4 mm, unannealed 205 °C ASTM D648 Relative Temp Index, Elec⁽¹⁾ 170 °C UL 746B Relative Temp Index, Mech w/impact $^{(1)}$ °C 170 UI 746B Relative Temp Index, Mech w/o impact (1) °C 170 UL 746B PHYSICAL ASTM D792 Specific Gravity 1.43 Melt Flow Rate, 337°C/6.6 kgf ASTM D1238 135 g/10 min ELECTRICAL Comparative Tracking Index (UL) {PLC} 4 PLC Code UI 746A Hot-Wire Ignition (HWI), PLC 1 ≥3 mm UL 746A Hot-Wire Ignition (HWI), PLC 2 ≥1.5 UL 746A mm High Amp Arc Ignition (HAI), PLC 3 ≥3 UL 746A mm

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS

Revision 20231109



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
High Amp Arc Ignition (HAI), PLC 4	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D495
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	<u>E121562-221097</u>	-	
Glow Wire Flammability Index, 1.5 mm	960	°C	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.5 mm	875	°C	IEC 60695-2-13
UL Recognized, 94V-0 Flame Class Rating	≥0.41	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 - 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 - 400	°C	
Rear - Zone 1 Temperature	330 - 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 - 70	rpm	
Shot to Cylinder Size	40 - 60	%	
Vent Depth	0.025 - 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.