

LNPT[™] ELCRIN[™] WF006XXPIQ

ERO15800

DESCRIPTION

LNP ELCRIN WF006XXPIQ compound is based on Polybutylene terephthalate (PBT) resin utilizing ELCRIN iQ upcycling technology containing minimum 38% Post-Consumer Recycling (PCR) weight content and 30% pre-consumer recycled glass fiber. Total sustainable content 67%. Added features of this grade include Excellent Strength, Stiffness, Dimensional Stability and Colorable. Potential applications may include handles, connectors.

GENERAL INFORMATION	
Features	Sustainable (Advanced Recycling), Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

TYPICAL PROPERTY VALUES

Revision 20240702

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	134	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	10500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	196	MPa	ISO 178
Flexural Modulus, 2 mm/min	9200	MPa	ISO 178
Tensile Stress, brk, Type I, 5 mm/min	137	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.8	%	ASTM D638
Tensile Modulus, 5 mm/min	10700	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	207	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	202	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	9400	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	51	kJ/m ²	ISO 180/1U
Izod Impact, unnotched, 23°C	810	J/m	ASTM D4812
Izod Impact, notched, 23°C	84	J/m	ASTM D256
Izod Impact, notched, -30°C	73	J/m	ASTM D256
Instrumented Impact Total Energy, 23°C	8	J	ASTM D3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	213	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	196	°C	ISO 75/Af
Vicat Softening Temp, Rate B/50	206	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	204	°C	ISO 306
HDT, 0.45 MPa, 3.2 mm, unannealed	214	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	201	°C	ASTM D648
CTE, -40°C to 40°C, flow	23	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	93	1/°C	ASTM E831
PHYSICAL ⁽¹⁾			
Density	1.59	g/cm ³	ISO 1183
Moisture Content	0.02	%	SABIC method
Melt Volume Rate, MVR at 250°C/5.0 kg	35	cm ³ /10 min	ISO 1133
Specific Gravity	1.60	-	ASTM D792
Mold Shrinkage, flow ⁽²⁾	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.9 – 1.1	%	SABIC method
ELECTRICAL			
Dielectric Constant, 2.5 GHz	3.58	-	SABIC method
Dissipation Factor, 2.5 GHz	0.008	-	SABIC method
Dielectric Constant, 5 GHz	3.61	-	SABIC method
Dissipation Factor, 5 GHz	0.008	-	SABIC method
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-104637766	-	-
UL Recognized, 94HB Flame Class Rating ⁽³⁾	≥0.84	mm	UL 94
INJECTION MOLDING ⁽¹⁾			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 265	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back pressure (Plastic Pressure)	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded articles.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.