

# LNPTM LUBRICOMPTM COMPOUND DL0029E

DL-4020 FR  
REGION AMERICAS

## DESCRIPTION

LNP LUBRICOMP DL0029E compound is based on Polycarbonate (PC) resin containing 10% PTFE. Added features of this grade include: Wear Resistant, Flame Retardant.

GENERAL INFORMATION	
Features	Flame Retardant, Wear resistant
Fillers	Unreinforced, PTFE
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 5 mm/min	56	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	47	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	5.7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	33	%	ASTM D638
Tensile Modulus, 5 mm/min	2240	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	86	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2330	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	2020	J/m	ASTM D4812
Izod Impact, notched, 23°C	119	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	46	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D648
CTE, -30°C to 30°C, flow	7.1E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	7.5E-05	1/°C	ASTM D696
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.31	-	ASTM D792
Density	1.31	g/cm <sup>3</sup>	ASTM D792

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption, (23°C/50% RH/24 hrs)	0.01	%	ASTM D570
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.6 – 0.8	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	0.8 – 1	%	ASTM D955
Wear Factor Washer	55	10 <sup>-10</sup> in <sup>4</sup> 5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.2	-	ASTM D3702 Modified: Manual
Static COF	0.14	-	ASTM D3702 Modified: Manual
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 315	°C	
Front - Zone 3 Temperature	310 – 320	°C	
Middle - Zone 2 Temperature	305 – 315	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.