

LNPT[™] THERMOCOMP[™] COMPOUND M10006P

DESCRIPTION

LNP THERMOCOMP[™] M10006P compound is based on Polypropylene (PP) resin containing non-halogenated Flame retardant suitable for use in composites and extrusion.

GENERAL INFORMATION	
Applications	Chemical & industrial systems
Features	Flame Retardant, Good Processability, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Impregnation (composites), Extrusion

INDUSTRY	SUB INDUSTRY
Industrial	Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	24	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.7	%	ISO 527
Tensile Modulus, 1 mm/min	2060	MPa	ISO 527
Flexural Strength, 2 mm/min	40	MPa	ISO 178
Flexural Modulus, 2 mm/min	1830	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	18	kJ/m ²	ISO 180/1U
PHYSICAL			
Melt Volume Rate, MVR at 230°C/2.16 kg	70	cm ³ /10 min	ISO 1133
EXTRUSION			
Drying Temperature	80	°C	
Drying Time	2 – 4	Hrs	
Barrel - Zone 1 Temperature	200 – 250	°C	
Melt Temperature	230 – 300	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.