

ULTEM™ RESIN 2100F

REGION EUROPE

DESCRIPTION

10% Glass fiber filled, standard flow Polyetherimide (Tg 217°C). ECO Conforming, UL94 V0 and 5VA listing. NSF 51 listing. WRAS certification in recognized colors.

This material is food contact compliant in most jurisdictions – exceptions may exist, request a declaration for details.

| GENERAL INFORMATION | |
|-----------------------|---|
| Features | Flame Retardant, Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Smoke and Toxicity, Amorphous, Low Shrinkage, Sustainable (bio-based offerings), Food contact, Non halogenated flame retardant, Electroplatable, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added |
| Fillers | Glass Fiber |
| Polymer Types | Polyetherimide (PEI) |
| Processing Techniques | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|----------------------------|---|
| Automotive | Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles |
| Building and Construction | Building Component, Water Management |
| Consumer | Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture |
| Electrical and Electronics | Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication |
| Hygiene and Healthcare | Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing |
| Industrial | Electrical, Material Handling, Textile, Eyewear |
| Mass Transportation | Rail |
| Packaging | Industrial Packaging |

TYPICAL PROPERTY VALUES

Revision 20250404

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--------------------------------------|----------------|-----------|--------------|
| MECHANICAL | | | |
| Taber Abrasion, CS-17, 1 kg | 15 | mg/1000cy | SABIC method |
| Tensile Stress, break, 5 mm/min | 115 | MPa | ISO 527 |
| Tensile Strain, break, 5 mm/min | 4 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 4500 | MPa | ISO 527 |
| Flexural Stress, break, 2 mm/min | 185 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 4500 | MPa | ISO 178 |
| Ball Indentation Hardness, H358/30 | 140 | MPa | ISO 2039-1 |
| IMPACT | | | |
| Izod Impact, unnotched 80*10*4 +23°C | 30 | kJ/m² | ISO 180/1U |
| Izod Impact, unnotched 80*10*4 -30°C | 30 | kJ/m² | ISO 180/1U |
| Charpy Impact, notched, 23°C | 7 | kJ/m² | ISO 179/2C |
| THERMAL | | | |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|--------------------------|------------|----------------|
| Thermal Conductivity | 0.24 | W/m·°C | ISO 8302 |
| CTE, 23°C to 150°C, flow | 3.0E-05 | 1/°C | ISO 11359-2 |
| CTE, 23°C to 150°C, xflow | 5.1E-05 | 1/°C | ISO 11359-2 |
| Ball Pressure Test, 125°C +/- 2°C | PASSES | - | IEC 60695-10-2 |
| Vicat Softening Temp, Rate A/50 | 223 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/50 | 212 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 217 | °C | ISO 306 |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm | 210 | °C | ISO 75/Be |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm | 205 | °C | ISO 75/Ae |
| Relative Temp Index, Elec ⁽¹⁾ | 170 | °C | UL 746B |
| Relative Temp Index, Mech w/impact ⁽¹⁾ | 170 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact ⁽¹⁾ | 170 | °C | UL 746B |
| PHYSICAL | | | |
| Mold Shrinkage on Tensile Bar, flow | 0.4 – 0.6 | % | SABIC method |
| Density | 1.34 | g/cm³ | ISO 1183 |
| Water Absorption, (23°C/saturated) | 1 | % | ISO 62-1 |
| Moisture Absorption (23°C / 50% RH) | 0.6 | % | ISO 62 |
| Melt Volume Rate, MVR at 360°C/5.0 kg | 9 | cm³/10 min | ISO 1133 |
| ELECTRICAL | | | |
| Volume Resistivity | ≥1.E+15 | Ω.cm | IEC 60093 |
| Surface Resistivity, ROA | >1.E+15 | Ω | IEC 60093 |
| Dielectric Strength, in oil, 0.8 mm | 34 | kV/mm | IEC 60243-1 |
| Dielectric Strength, in oil, 1.6 mm | 27 | kV/mm | IEC 60243-1 |
| Dielectric Strength, in oil, 3.2 mm | 15 | kV/mm | IEC 60243-1 |
| Relative Permittivity, 1 MHz | 2.9 | - | IEC 60250 |
| Dissipation Factor, 50/60 Hz | 0.0009 | - | IEC 60250 |
| Dissipation Factor, 1 MHz | 0.0025 | - | IEC 60250 |
| Dissipation Factor, 2450 MHz | 0.0046 | - | IEC 60250 |
| Comparative Tracking Index ⁽²⁾ | 150 | V | IEC 60112 |
| Comparative Tracking Index, M ⁽²⁾ | 100 | V | IEC 60112 |
| Relative Permittivity, 50/60 Hz | 3 | - | IEC 60250 |
| Comparative Tracking Index (UL) {PLC} | 4 | PLC Code | UL 746A |
| Hot-Wire Ignition (HWI), PLC 1 | ≥3 | mm | UL 746A |
| Hot-Wire Ignition (HWI), PLC 2 | ≥1.5 | mm | UL 746A |
| High Amp Arc Ignition (HAI), PLC 3 | ≥1.5 | mm | UL 746A |
| High Amp Arc Ignition (HAI), PLC 4 | ≥3 | mm | UL 746A |
| High Voltage Arc Track Rate {PLC} | 2 | PLC Code | UL 746A |
| Arc Resistance, Tungsten {PLC} | 6 | PLC Code | ASTM D495 |
| FLAME CHARACTERISTICS ⁽¹⁾ | | | |
| UL Yellow Card Link | <u>E121562-502535</u> | - | - |
| UL Yellow Card Link 2 | <u>E121562-102518191</u> | - | - |
| UL Recognized, 94-5VA Flame Class Rating | ≥1.9 | mm | UL 94 |
| UL Recognized, 94V-0 Flame Class Rating | ≥0.41 | mm | UL 94 |
| Glow Wire Flammability Index 960°C, passes at ⁽²⁾ | 3.2 | mm | IEC 60695-2-12 |
| Oxygen Index (LOI) | 46 | % | ISO 4589 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| INJECTION MOLDING | | | |
| Drying Temperature | 150 | °C | |
| Drying Time | 4 – 6 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 370 – 410 | °C | |
| Nozzle Temperature | 350 – 405 | °C | |
| Front - Zone 3 Temperature | 360 – 415 | °C | |
| Middle - Zone 2 Temperature | 350 – 405 | °C | |
| Rear - Zone 1 Temperature | 340 – 395 | °C | |
| Hopper Temperature | 80 – 120 | °C | |
| Mold Temperature | 140 – 180 | °C | |

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(2) Value shown here is based on internal measurement.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.