NORYL GTX™ RESIN GTX202

REGION ASIA

DESCRIPTION

NORYL GTX202 resin is a non-reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade exhibits excellent chemical resistance and excellent paintability.

GENERAL INFORMATION	
Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, High stiffness/Strength, High temperature resistance, Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PA (PPE+Nylon)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Exteriors, Recreational/Specialty Vehicles
Consumer	Personal Recreation

TYPICAL PROPERTY VALUES

Revision 20260818

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 50 mm/min	59	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	56	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	9	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	52	%	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	89	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	2240	MPa	ASTM D790
Hardness, Rockwell R	118	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	19	mg/1000cy	ASTM D1044
IMPACT [1]			
Izod Impact, Unnotched			
23°C	3204	J/m	ASTM D4812
-30°C	3204	J/m	ASTM D4812
-40°C	3204	J/m	ASTM D4812
Izod impact, notched			
23°C	272	J/m	ASTM D256
-30°C	117	J/m	ASTM D256
-40°C	53	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	46	J	ASTM D3763
Instrumented Dart Impact Energy @ peak, -30°C	36	J	ASTM D3763
Instrumented Impact Energy @ peak, -40°C	19	J	ASTM D3763
THERMAL [1]			

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	232	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	155	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	127	°C	ASTM D648
CTE, -20°C to 150°C, flow	9.00E-05	1/°C	ASTM E831
PHYSICAL [1]			
Specific Gravity	1.08	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.4	%	ASTM D570
Water Absorption, (23°C/Saturated)	3.6	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm [2]	0.9 – 1.2	%	SABIC method
Mold Shrink, flow, annealed 130C 1hr [2]	1.1 – 1.5	%	ASTM D955
Mold Shrinkage, xflow, 3.2 mm [2]	0.8 – 1.1	%	SABIC method
INJECTION MOLDING [3]			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	270 – 300	°C	
Middle - Zone 2 Temperature	265 – 300	°C	
Rear - Zone 1 Temperature	260 – 300	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved