

NORYL GTX™ RESIN GTX918W

REGION ASIA

DESCRIPTION

NORYL GTX918W resin is a non-reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade exhibits high heat resistance, excellent chemical resistance, and high melt flow. NORYL GTX918W resin may be an excellent candidate for automotive under-the-hood and electrical applications requiring the retention of properties while under thermal load.

GENERAL INFORMATION	
Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, High stiffness/Strength, High temperature resistance, Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PA (PPE+Nylon)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Electrical and Electronics	Electronic Components, Lighting
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20241015

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	53	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	98	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2360	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	202	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	40	J	ASTM D3763
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	188	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	148	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Specific Gravity	1.09	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	1.3 – 1.6	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽²⁾	1 – 1.3	%	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.07	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Minimum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	270 – 295	°C	
Front - Zone 3 Temperature	265 – 295	°C	
Middle - Zone 2 Temperature	260 – 295	°C	
Rear - Zone 1 Temperature	255 – 295	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.