

# ULTEM™ RESIN 2200R

REGION AMERICAS

## DESCRIPTION

20% Glass fiber filled, standard flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming, UL94 V0 and 5VA listing.

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles
Building and Construction	Building Component, Water Management
Consumer	Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture
Electrical and Electronics	Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication
Hygiene and Healthcare	Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial	Electrical, Material Handling, Textile, Eyewear
Mass Transportation	Rail
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, brk, Type I, 5 mm/min	131	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D638
Tensile Modulus, 5 mm/min	6890	MPa	ASTM D638
Flexural Stress, brk, 2.6 mm/min, 100 mm span	227	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	6890	MPa	ASTM D790
Hardness, Rockwell M	114	-	ASTM D785
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	480	J/m	ASTM D4812
Izod Impact, notched, 23°C	90	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	512	J/m	ASTM D256
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	220	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
CTE, -20°C to 150°C, flow	2.1E-05	1/°C	ASTM E831
Relative Temp Index, Elec <sup>(1)</sup>	170	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	170	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	170	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.42	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.19	%	ASTM D570
Water Absorption, (23°C/Saturated)	1.1	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.5	%	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 337°C/6.6 kgf	6.5	g/10 min	ASTM D1238
<b>ELECTRICAL</b>			
Volume Resistivity	7.E+16	Ω.cm	ASTM D257
Dielectric Strength, in oil, 1.6 mm	26.3	kV/mm	ASTM D149
Relative Permittivity, 1 kHz	3.5	-	ASTM D150
Dissipation Factor, 1 kHz	0.0015	-	ASTM D150
Dissipation Factor, 2450 MHz	0.0049	-	ASTM D150
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-221093</a>	-	-
UL Yellow Card Link 2	<a href="#">E121562-502535</a>	-	-
UL Recognized, 94-5VA Flame Class Rating	≥1.9	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.41	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
Oxygen Index (LOI)	50	%	ASTM D2863
NBS Smoke Density, Flaming, Ds 4 min	1.3	-	ASTM E662
<b>INJECTION MOLDING</b>			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.