

LNPTTM THERMOCOMPTM COMPOUND DF002AT

DESCRIPTION

LNP THERMOCOMP DF002AT compound is based on Polycarbonate (PC) resin containing 10% glass fiber. Added features of this grade include: Transparent/Translucent, High stiffness/Strength

GENERAL INFORMATION	
Features	Transparent/Translucent, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Interiors
Consumer	Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets

TYPICAL PROPERTY VALUES

Revision 20250716

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	71.2	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.8	%	ASTM D638
Tensile Modulus, 5 mm/min	3600	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	122	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3400	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	71	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.9	%	ISO 527
Tensile Modulus, 1 mm/min	3600	MPa	ISO 527
Flexural Strength, 2 mm/min	117	MPa	ISO 178
Flexural Modulus, 2 mm/min	3400	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	162	J/m	ASTM D256
Izod Impact, notched, 0°C	117	J/m	ASTM D256
Izod Impact, notched, -30°C	95.1	J/m	ASTM D256
Izod Impact, unnotched, 23°C	733	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	911	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	13.9	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9.22	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	44.5	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	53.8	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14.9	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	7.1	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	53.1	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	65.5	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	116	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	117	°C	ISO 75/Af
Vicat Softening Temp, Rate A/120	136	°C	ASTM D1525
Vicat Softening Temp, Rate A/50	134	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	127	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	126	°C	ASTM D1525
Vicat Softening Temp, Rate A/120	136	°C	ISO 306
Vicat Softening Temp, Rate A/50	134	°C	ISO 306
Vicat Softening Temp, Rate B/120	126	°C	ISO 306
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
CTE, -40°C to 40°C, flow	4.243E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.278E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	3.966E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.06E-05	1/°C	ISO 11359-2
PHYSICAL ⁽¹⁾			
Density	1.24	g/cm ³	ASTM D792
Mold Shrinkage, flow ⁽²⁾	0.33	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.48	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	11	g/10 min	ASTM D1238
Moisture Absorption, (23°C/50% RH/24hrs)	0.06	%	ISO 62-4
ELECTRICAL ⁽¹⁾			
Dielectric Constant, 1.1 GHz	2.93	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0081	-	SABIC method
Dielectric Constant, 1.9 GHz	2.95	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0083	-	SABIC method
Dielectric Constant, 5 GHz	2.92	-	SABIC method
Dissipation Factor, 5 GHz	0.0089	-	SABIC method
Dielectric Constant, 10 GHz	2.94	-	SABIC method
Dissipation Factor, 10 GHz	0.0091	-	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	100	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 320	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	290 – 310	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	270 – 280	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.