LNP™ THERMOTUF™ COMPOUND WF009NAR

DESCRIPTION

LNP THERMOTUF WF009NAR compound is based on Polybutylene Terephthalate (PBT) resin containing 45% glass fiber. Added features of this grade include: Impact Modified, Good Metal Bonding Strength and Good Chemical Resistance targeted for Nano-Molding Technology (NMT) applications.

GENERAL INFORMATION	
Features	Chemical Resistance, Nano molding technology, High stiffness/Strength, Impact resistant
Fillers	Glass Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260407

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, brk, Type I, 5 mm/min	162	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.1	%	ASTM D638
Tensile Modulus, 5 mm/min	14900	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	242	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	237	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	13700	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	172	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	15700	MPa	ISO 527
Flexural Stress, break, 2 mm/min	264	MPa	ISO 178
Flexural Modulus, 2 mm/min	13000	MPa	ISO 178
Bonding strength (TRI) , 5 mm/min, Type A	42	MPa	ISO 19095
IMPACT [1]			
Izod Impact, unnotched, 23°C	980	J/m	ASTM D4812
Izod Impact, notched, 23°C	123	J/m	ASTM D256
Izod Impact, notched, -30°C	115	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	60	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m²	ISO 180/1A
Charpy Impact, unnotched, 23°C	69	kJ/m²	ISO 179/2C
Charpy Impact, notched, 23°C	12	kJ/m²	ISO 179/2C
Charpy Impact, notched, -30°C	11	kJ/m²	ISO 179/2C

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL [1]			
Vicat Softening Temp, Rate B/50	216	°C	ASTM D1525
HDT, 1.82 MPa, 6.4 mm, unannealed	208	°C	ASTM D648
Vicat Softening Temp, Rate A/50	215	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	207	°C	ISO 75/Af
CTE, -40°C to 40°C, flow	1.7E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.6E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec [2]	75	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	75	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	75	°C	UL 746B
PHYSICAL [1]			
Density	1.7	g/cm³	ASTM D792
Melt Volume Rate			
275°C/5 kg	17	cm³/10 min	ISO 1133
285°C/5.0 kg	27	cm³/10 min	ISO 1133
ELECTRICAL [1]			
Dielectric Constant			
1.1 GHz	3.93	-	SABIC method
1.9 GHz	3.92	-	SABIC method
Dissipation Factor			
1.1 GHz	0.00792	-	SABIC method
1.9 GHz	0.00769	-	SABIC method
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E207780-103376952	-	-
UL Recognized, 94HB Flame Class Rating	≥0.7	mm	UL 94
INJECTION MOLDING [3]			
Drying Temperature	100 – 120	°C	
Drying Time	4 – 8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 285	°C	
Nozzle Temperature	265 – 285	°C	
Front - Zone 3 Temperature	265 – 285	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	250 – 270	°C	
Mold Temperature	120 – 160	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

© 2026 Copyright by SABIC. All rights reserved

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved