

# NORYL™ RESIN GFN2L

REGION ASIA

## DESCRIPTION

NORYL GFN2L resin is a 20% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability.

GENERAL INFORMATION	
Features	Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Industrial General

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	98	MPa	SABIC - Japan Method
Tensile Strain, break	8 – 10	%	SABIC - Japan Method
Flexural Stress	142	MPa	ASTM D790
Flexural Modulus	5570	MPa	ASTM D790
Hardness, Rockwell R	124	-	ASTM D785
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	107	J/m	ASTM D256
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	139	°C	ASTM D648
CTE, -30°C to 30°C	0.000028 – 0.000045	1/°C	TMA
Relative Temp Index, Elec <sup>(2)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	65	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.23	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm <sup>(3)</sup>	0.2 – 0.4	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	11.1	g/10 min	ASTM D1238
<b>ELECTRICAL <sup>(1)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Surface Resistivity	1.E+16	Ω	ASTM D257
Relative Permittivity, 50/60 Hz	2.86	-	ASTM D150
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E45587-237021</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 325	°C	
Nozzle Temperature	300 – 325	°C	
Front - Zone 3 Temperature	290 – 325	°C	
Middle - Zone 2 Temperature	275 – 320	°C	
Rear - Zone 1 Temperature	265 – 315	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.