LNP™ THERMOCOMP™ Compound QF0069

QF-1006 FR-1
REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP QF0069 compound is based on Nylon 6/10 resin containing 30% glass fiber. Added features of this grade include: Flame Retardant.

GENERAL INFORMATION	
Features	Flame Retardant, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polyamide 610 (Nylon 610)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Aerospace
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yield	150	MPa	ASTM D638
Tensile Stress, break	150	MPa	ASTM D638
Tensile Strain, yield	2	%	ASTM D638
Tensile Strain, break	2	%	ASTM D638
Tensile Modulus, 50 mm/min	11030	MPa	ASTM D638
Flexural Stress	199	MPa	ASTM D790
Flexural Modulus	9650	MPa	ASTM D790
Tensile Stress, yield	145	MPa	ISO 527
Tensile Stress, break	145	MPa	ISO 527
Tensile Strain, yield	1.8	%	ISO 527
Tensile Strain, break	1.8	%	ISO 527
Tensile Modulus, 1 mm/min	11020	MPa	ISO 527
Flexural Stress	197	MPa	ISO 178
Flexural Modulus	9000	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched, 23°C	603	J/m	ASTM D4812
Izod Impact, notched, 23°C	64	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	9	J	ASTM D3763
Multiaxial Impact	2	J	ISO 6603

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 +23°C	37	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	201	°C	ASTM D648
CTE, -40°C to 40°C, flow	3.96E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.66E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	4.0E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.70E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	218	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	196	°C	ISO 75/Af
Relative Temp Index, Elec [2]	65	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	65	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	65	°C	UL 746B
PHYSICAL [1]			
Density	1.56	g/cm³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1	%	ASTM D570
Mold Shrinkage, flow, 24 hrs [3]	0.2 – 0.4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs [3]	0.8 – 1	%	ASTM D955
Mold Shrinkage, flow, 24 hrs [3]	0.29	%	ISO 294
Mold Shrinkage, xflow, 24 hrs [3]	0.86	%	ISO 294
Density	1.56	g/cm³	ISO 1183
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E121562-101344701	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.12 – 0.2	%	
Melt Temperature	270 – 275	°C	
Front - Zone 3 Temperature	270 – 280	°C	
Middle - Zone 2 Temperature	260 – 270	°C	
Rear - Zone 1 Temperature	250 – 260	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

© 2026 Copyright by SABIC. All rights reserved

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved