

LNPTTM LUBRILLOYTM COMPOUND N2000

DESCRIPTION

LNP LUBRILLOY N2000 compound is based on unfilled Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS). Added features of this grade include excellent BSR (Buzz, Squeak, Rattle) performance. Custom colorable, low gloss, internally lubricated without silicones or fluorinated polymers. Good impact and flow properties.

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 1 mm/min	2058	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	46	MPa	ISO 527
Tensile Stress, break, 50 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Flexural Modulus, 2 mm/min	2016	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	37	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	16	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	31	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	16	kJ/m ²	ISO 179/1eA
Izod Impact, notched, 23°C	39	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	102	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.11	g/cm ³	ISO 1183
Dynamic COF	0.37	-	ASTM D3702 Modified: Manual
Wear Factor Washer	85	10 ⁻⁴ -10 in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Specific Gravity	1.12	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.12	%	ASTM D570
Mold Shrinkage, flow ⁽²⁾	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.4 – 0.6	%	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80 – 110	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.012 – 0.02	%	
Melt Temperature	240 – 265	°C	
Rear - Zone 1 Temperature	240 – 265	°C	
Middle - Zone 2 Temperature	240 – 265	°C	
Front - Zone 3 Temperature	240 – 265	°C	
Nozzle Temperature	240 – 265	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Vent Depth	0.038 – 0.051	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.