

NORYL™ RESIN N190

REGION EUROPE

DESCRIPTION

NORYL N190 resin is a non-reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of 5VA at 3mm and V0 at 1.5mm along with UL746C Outdoor Suitability rating of F1. NORYL N190 resin exhibits high impact strength, dimensional stability, hydrolytic stability, and very low moisture absorption. This material is an excellent candidate for a variety of applications such as solar frames, unattended power supply (UPS) inverter/charger, indoor and outdoor electrical enclosures / housings / connectors, and wall plates / sockets / switches. *This grade is also referred to as NORYL N1900 in several regions.

GENERAL INFORMATION	
Features	Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Electrical and Electronics	Energy Management, Electronic Components
Industrial	Electrical, Defense

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	20	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Ball Indentation Hardness, H358/30	87	MPa	ISO 2039-1
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
Thermal Conductivity	0.25	W/m·°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Ball Pressure Test, approximate maximum	95	°C	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	110	°C	ISO 306
Vicat Softening Temp, Rate B/50	95	°C	ISO 306
Vicat Softening Temp, Rate B/120	105	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	90	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	80	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽²⁾	95	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	95	°C	UL 746B
PHYSICAL ⁽¹⁾			
Mold Shrinkage on Tensile Bar, flow ⁽³⁾	0.5 – 0.7	%	SABIC method
Density	1.1	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.32	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 280°C/2.16 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Volume Resistivity	1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Relative Permittivity, 1 MHz	2.6	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0004	-	IEC 60250
Dissipation Factor, 1 MHz	0.0009	-	IEC 60250
Comparative Tracking Index ⁽⁴⁾	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.7	-	IEC 60250
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E45329-236763	-	-
UL Recognized, 94-5VA Flame Class Rating	≥3	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at ⁽⁴⁾	3.2	mm	IEC 60695-2-12
UV-light, water exposure/immersion	F1	-	UL 746C
Oxygen Index (LOI)	30	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	80 – 100	°C	
Drying Time	2 – 3	Hrs	
Melt Temperature	260 – 280	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	240 – 260	°C	
Rear - Zone 1 Temperature	220 – 240	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 80	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Value shown here is based on internal measurement.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.