

LNPTM ELCRINTM WF008NiQ

DESCRIPTION

LNP ELCRIN WF008NiQ is an iQ PBT/glass fiber compound for nano-molding technology (NMT) application. Added features of this material include: >20% PCR content, high modulus, excellent metal bonding force, good surface quality, high impact, good adhesion and good color stability during anodizing process.

GENERAL INFORMATION	
Features	Chemical Resistance, High Flow, Sustainable (Advanced Recycling), Electroplatable, Nano molding technology, High stiffness/Strength, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Consumer	Personal Accessory
Electrical and Electronics	Electrical Devices and Displays, Electrical Components and Infrastructure

TYPICAL PROPERTY VALUES

Revision 20260820

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	150	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D638
Tensile Modulus, 5 mm/min	13200	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	165	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	2.8	%	ASTM D638
Tensile Modulus, 50 mm/min	13200	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	225	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	10900	MPa	ASTM D790
Tensile Modulus, 1 mm/min	13000	MPa	ISO 527
Tensile Stress, break, 5 mm/min	151	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Stress, break, 50 mm/min	162	MPa	ISO 527
Tensile Strain, break, 50 mm/min	2.6	%	ISO 527
Flexural Strength, 2 mm/min	223	MPa	ISO 178
Flexural Modulus, 2 mm/min	11000	MPa	ISO 178
Bonding Strength ("T" treatment, shear type)	34	MPa	ISO 19095
Bonding strength (TRI) , 5 mm/min, Type A	38	MPa	ISO 19095
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	160	J/m	ASTM D256
Izod Impact, notched, -30°C	135	J/m	ASTM D256
Izod Impact, unnotched, 23°C	1000	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	15	kJ/m²	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 -30°C	14	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	53	kJ/m ²	ISO 180/1U
Charpy Impact, notched, 23°C	15.5	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	14.5	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, 23°C	63	kJ/m ²	ISO 179/2C
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	217	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	206	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	207	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	218	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	206	°C	ISO 75/Af
CTE, -40°C to 40°C, flow	1.9E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.4E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	200	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	198	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	201	°C	ISO 306
Vicat Softening Temp, Rate B/120	196	°C	ISO 306
Relative Temp Index, Elec ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	75	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.6	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.03	%	ISO 62-1
Moisture Absorption, (23°C/50% RH/24hrs)	0.01	%	ISO 62-4
Melt Flow Rate			
275°C/2.16 kgf	11	g/10 min	ASTM D1238
275°C/5 kgf	39	g/10 min	ASTM D1238
Melt Volume Rate			
275°C/2.16 kg	10	cm ³ /10 min	ISO 1133
275°C/5 kg	30	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow ⁽³⁾	0.2	%	SABIC method
Mold Shrinkage, xflow ⁽³⁾	0.5	%	SABIC method
ELECTRICAL ⁽¹⁾			
Dielectric Constant			
1.1 GHz	3.9	-	SABIC method
1.9 GHz	3.88	-	SABIC method
5 GHz	3.91	-	SABIC method
10 GHz	3.84	-	SABIC method
20 GHz	3.78	-	SABIC method
Dissipation Factor			
1.1 GHz	0.0118	-	SABIC method
1.9 GHz	0.0115	-	SABIC method
5 GHz	0.0105	-	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
10 GHz	0.0095	-	SABIC method
20 GHz	0.0112	-	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	<u>E207780-104592047</u>	-	-
UL Recognized, 94HB Flame Class Rating	≥0.7	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Hopper Temperature	40 – 60	°C	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	255 – 275	°C	
Front - Zone 3 Temperature	250 – 275	°C	
Middle - Zone 2 Temperature	250 – 275	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Mold Temperature	100 – 150	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.