

LNPTM STAT-KONTM COMPOUND RX05489

RCFL-4536
REGION ASIA

DESCRIPTION

LNP STAT-KON RX05489 compound is based on Nylon 6/6 resin containing 10% carbon fiber, 20% glass fiber, 15% PTFE/silicone. Added features of this grade include: Electrically Conductive, Wear Resistant.

GENERAL INFORMATION	
Features	Electrically Conductive, Wear resistant, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber, Glass Fiber, PTFE/Silicone
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	171	MPa	ASTM D638
Tensile Strain, break	2.6	%	ASTM D638
Tensile Modulus, 50 mm/min	14940	MPa	ASTM D638
Flexural Stress	296	MPa	ASTM D790
Flexural Modulus	14410	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	807	J/m	ASTM D4812
Izod Impact, notched, 23°C	85	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	246	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.41	g/cm ³	ASTM D792
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽²⁾	1.E+01 – 1.E+06	Ω	ASTM D257

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurement meets requirements as specified in ASTM D4496.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.