

# LNPTM KONDUIT™ COMPOUND PX10323H

PX10323

REGION ASIA

## DESCRIPTION

LNP KONDUIT PX10323H compound is based on Nylon 6 resin containing glass fiber. Added features of this grade include: Thermally Conductive and Healthcare.

GENERAL INFORMATION	
Features	Thermally Conductive, Healthcare/Formula lock
Fillers	Glass Fiber
Polymer Types	Polyamide 6 (Nylon 6)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL <sup>(1)</sup>			
Tensile Stress, brk, Type I, 5 mm/min	70	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	0.9	%	ASTM D638
Tensile Modulus, 5 mm/min	13700	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	96	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	95	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	14200	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	73	MPa	ISO 527
Tensile Strain, break, 5 mm/min	0.8	%	ISO 527
Tensile Modulus, 1 mm/min	14000	MPa	ISO 527
Flexural Stress, break, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	14300	MPa	ISO 178
Impact Strength	3.7 – 6.8	kJ/m <sup>2</sup>	ISO R179
IMPACT <sup>(1)</sup>			
Izod Impact, unnotched, 23°C	73	J/m	ASTM D4812
Izod Impact, notched, 23°C	30	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	6	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m <sup>2</sup>	ISO 180/1A
THERMAL <sup>(1)</sup>			
HDT, 1.82 MPa, 6.4 mm, unannealed	204	°C	ASTM D648
CTE, 40°C to 120°C, flow	1.24E-05	1 /°C	ASTM E831
CTE, 40°C to 120°C, xflow	7.27E-05	1 /°C	ASTM E831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Thermal Conductivity through-plane, 60*60*3mm plaque	1.5	W/m-K	ISO 22007-2
Thermal Conductivity in-plane, 60*60*3mm plaque	18	W/m-K	ISO 22007-2
Thermal Conductivity through-plane, 10*10*3mm sample	3.5	W/m-K	ASTM E1461-07
Thermal Conductivity in-plane, 25*0.4mm disc	15	W/m-K	ASTM E1461-07
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	217	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	201	°C	ISO 75/Af
PHYSICAL <sup>(1)</sup>			
Density	1.61	g/cm <sup>3</sup>	ASTM D792
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	0.22	%	ASTM D955
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
ELECTRICAL <sup>(1)</sup>			
Surface Resistivity	1.05E+06	Ω	ASTM D257
FLAME CHARACTERISTICS			
Glow Wire Flammability Index 850°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at	1.6	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
INJECTION MOLDING <sup>(3)</sup>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	270 – 295	°C	
Front - Zone 3 Temperature	270 – 290	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 275	°C	
Mold Temperature	85 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	20 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.