

LNPTM THERMOCOMPTM COMPOUND GF004

GF-1004

REGION EUROPE

DESCRIPTION

LNP THERMOCOMP GF004 compound is based on Polysulfone (PSU) resin containing 20% glass fiber.

GENERAL INFORMATION	
Features	High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polysulfone (PSU)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical, Defense

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	103	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Flexural Stress, break, 2 mm/min	153	MPa	ISO 178
Flexural Modulus, 2 mm/min	6500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	2.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.8E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	185	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	182	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.4	g/cm ³	ISO 1183

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.