

LNPT[™] STAT-LOY[™] COMPOUND N30009

PCA-FR
REGION EUROPE

DESCRIPTION

LNP STAT-LOY N30009 compound is based on Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend containing proprietary fillers. Added features of this grade include: Permanently Anti-Static, Flame Retardant.

| GENERAL INFORMATION | |
|----------------------------|------------------------------|
| Features | Flame Retardant, Antistatic |
| Fillers | Unreinforced |
| Polymer Types | Polycarbonate + ABS (PC+ABS) |
| Processing Techniques | Injection Molding |
| INDUSTRY | SUB INDUSTRY |
| Electrical and Electronics | Electronic Components |
| Industrial | Material Handling |

TYPICAL PROPERTY VALUES

Revision 20241028

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|-----------------|-------------------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, yield, 5 mm/min | 45 | MPa | ISO 527 |
| Tensile Strain, break, 5 mm/min | >10 | % | ISO 527 |
| Flexural Stress, yield, 2 mm/min | 55 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 1700 | MPa | ISO 178 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, notched 80*10*4 +23°C | 15 | kJ/m ² | ISO 180/1A |
| THERMAL ⁽¹⁾ | | | |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 100 | °C | ISO 75/Af |
| PHYSICAL ⁽¹⁾ | | | |
| Mold Shrinkage, flow ⁽²⁾ | 0.5 – 0.7 | % | SABIC method |
| Density | 1.25 | g/cm ³ | ISO 1183 |
| ELECTRICAL ⁽¹⁾ | | | |
| Surface Resistivity ⁽³⁾ | 1.E+10 – 1.E+12 | Ω | ASTM D257 |
| INJECTION MOLDING ⁽⁴⁾ | | | |
| Drying Temperature | 80 | °C | |
| Drying Time | 4 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 225 – 270 | °C | |
| Nozzle Temperature | 250 – 260 | °C | |
| Front - Zone 3 Temperature | 240 – 265 | °C | |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Middle - Zone 2 Temperature | 225 – 250 | °C | |
| Rear - Zone 1 Temperature | 210 – 230 | °C | |
| Mold Temperature | 40 – 55 | °C | |
| Back Pressure | 0.2 – 0.3 | MPa | |
| Screw Speed | 30 – 60 | rpm | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Measurement meets requirements as specified in ASTM D4496.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.