

# ULTEM™ RESIN 4000

REGION AMERICAS

## DESCRIPTION

Glass fiber, PTFE, and Graphite filled, standard flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 listing.

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles
Building and Construction	Building Component, Water Management
Consumer	Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture
Electrical and Electronics	Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication
Hygiene and Healthcare	Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial	Electrical, Material Handling, Textile, Eyewear
Mass Transportation	Rail
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, brk, Type I, 5 mm/min	82	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.2	%	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	113	MPa	ASTM D790
Flexural Stress, brk, 2.6 mm/min, 100 mm span	137	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	8820	MPa	ASTM D790
Hardness, Rockwell M	85	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	33	mg/1000cy	ASTM D1044
PV Limit, 0.51 m/s	2.1	MPa-m/s	SABIC method
K-factor xE-10, PV=2000 psi-fpm vs Steel	50	-	SABIC method
K-factor xE-10, PV=2000 psi-fpm vs Self	1900	-	SABIC method
Coefficient of Friction on steel, Static	0.25	-	ASTM D1894
Coefficient of Friction on steel, Kinetic	0.24	-	ASTM D1894
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	160	J/m	ASTM D4812
Izod Impact, notched, 23°C	64	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	170	J/m	ASTM D256
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	233	°C	ASTM D1525
HDT, 1.82 MPa, 6.4 mm, unannealed	212	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.62E-05	1/°C	ASTM E831
CTE, -20°C to 150°C, flow	1.62E-05	1/°C	ASTM E831
Relative Temp Index, Elec <sup>(1)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	105	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	105	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.67	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.11	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.3	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	3.1	g/10 min	ASTM D1238
<b>ELECTRICAL</b>			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-221109</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	0.84	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	135	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	10	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 370	°C	
Nozzle Temperature	350 – 370	°C	
Front - Zone 3 Temperature	350 – 370	°C	
Middle - Zone 2 Temperature	345 – 365	°C	
Rear - Zone 1 Temperature	340 – 360	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.