

LNPTM STAT-KONTM COMPOUND WX06322

DESCRIPTION

LNP STAT-KON WX06322 compound is based on Polybutylene Terephthalate (PBT) resin containing glass fiber and carbon fiber. Added features of this grade include: Electrically Conductive, Flame Retardant, Low Warpage.

GENERAL INFORMATION	
Features	Flame Retardant, Electrically Conductive, Low Warpage, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber, Glass Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20241025

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Flexural Stress, yield, 6.4 mm	202	MPa	ASTM D790
Flexural Modulus, 6.4 mm	11450	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	78	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 6.4 mm, unannealed	204	°C	ASTM D648
CTE, 23°C to 60°C, flow	1.32E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.25E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	75	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.55	-	ASTM D792
Mold Shrinkage, flow, 1.5-3.2 mm ⁽³⁾	0.17	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm ⁽³⁾	0.55	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽⁴⁾	1.3E+06	Ω	ASTM D257
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-101283813	-	-
UL Recognized, 94V-0 Flame Class Rating	≥2	mm	UL 94
INJECTION MOLDING ⁽⁵⁾			
Drying Temperature	120	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Measurement meets requirements as specified in ASTM D4496.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.