

LNPTTM THERMOCOMPTM COMPOUND UF00AAS

DESCRIPTION

LNP THERMOCOMP UF00AAS compound is based on Polyphthalamide (PPA) resin containing 50% glass fiber. Added features of this grade include: Heat Stabilized.

GENERAL INFORMATION	
Features	Heat Stabilized, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphthalamide (PPA)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	234	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Flexural Stress, yield, 2 mm/min	365	MPa	ISO 178
Flexural Modulus, 2 mm/min	14800	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	65	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	269	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	0.1 – 0.3	%	SABIC method
Density	1.63	g/cm ³	ISO 1183
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15	%	
Melt Temperature	315 – 330	°C	
Front - Zone 3 Temperature	325 – 340	°C	
Middle - Zone 2 Temperature	315 – 325	°C	
Rear - Zone 1 Temperature	310 – 320	°C	
Mold Temperature	140 – 165	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.